



250 Chester Street
Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FBA 8318 GL
SUPPORT: PET FOAM
SUBSTRATE: DuPont RK8148
CERT NO: 230530 - 1252


FORD WSS-M3G201-A2
OEM Rev Date: Oct 18



TEST PARAMETERS:

SECTION : 3.5 Peel Adhesion	ASTM D 3330-04 10		
Specification: 300 N / m		<u>Results</u>	<u>Status</u>
3.5.1, Peel Adhesion, Initial, Room Temp		362.2	Pass
SECTION : 3.5 Peel Adhesion	ASTM D 3330-04 10		
Specification: 417 N / m		<u>Results</u>	<u>Status</u>
3.5.2, Peel Adhesion, RH, 14 days @ 38°C / 95-100%		493.6	Pass
SECTION : 3.5 Peel Adhesion	ASTM D 3330-04 10		
Specification: 417 N / m		<u>Results</u>	<u>Status</u>
3.5.3, Peel Adhesion, Heat Aged, 14 days @ 80°C		581.9	Pass
SECTION : 3.5 Peel Adhesion	ASTM D 3330-04 10		
Specification: 417 N / m		<u>Results</u>	<u>Status</u>
3.5.4, Peel Adhesion, 30 minutes @ 120°C		623.2	Pass
SECTION : 3.5 Peel Adhesion	ASTM D 3330-04 10		
Specification: 417 N / m		<u>Results</u>	<u>Status</u>
3.5.5, Peel Adhesion, Cycles (7X)		593.8	Pass
3 hrs @ 80° C			
1 hrs @ 23° C / 50% RH			
3 hrs @ -40° C			
1 hrs @ 23° C / 50% RH			
16 hrs @ 38° C / 95% RH			
16 hrs @ 38° C / 95% RH			
4 hrs @ -40° C			
4 hrs @ 90° C			
SECTION : 3.6 Liner Removal	ASTM D 3330-04 10		
Specification: < 3.6 N / m		<u>Results</u>	<u>Status</u>
3.6.1, Liner Removal, Initial		0.011	Pass
SECTION : 3.7 Flammability	ISO 3795* / SAE J369*		
Specification: < 100 mm / min		<u>Results</u>	<u>Status</u>
3.7.1 Burn Rate, Component, Flammability,			Pass

CERTIFIED BY:


Dave Nichols Jr, Automotive Lab Technician

RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request in full, without the written approval of the Avery Dennison Performance Tapes. by personnel with appropriate training and professional experience. dated for the calibrations or tests marked *.

ISSUE DATE: 1-1-25