



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FT 1126 12 PT BD
SUPPORT: 2# XLPE FOAM
SUBSTRATE: ABS
CERT NO.: 221213 - 1206

FORD WSS-M99P48-B3
OEM Rev Date: Feb 21

Foam Performance, Pressure Sensitive Adhesive Tape (Interior, Exterior, Underhood, Underhood)

Interior
At or Above the Belt Line



TAPE REQUIREMENTS:

SECTION: 3.2.1 Odor

3.2.1 Odor, Condition 1 - 24 hrs @ RT, Deionized Water
3.2.1 Odor, Condition 2 - 24 hrs @ 40°C, Deionized Water
3.2.1 Odor, Condition 3 - 2 hrs @ 65°C

Specification	FLTM BO 131-03	Results	Status
Rating 3 Max		Slightly Perceptible, 1.5	Pass
Rating 3 Max		Slightly Perceptible, 1.5	Pass
Rating 3 Max		Very Perceptible, But Not Disturbing, 3	Pass

SECTION: 3.2.2 Fogging, Photometric

3.2.2, 3 hrs @ 100°C, 21°C Cooling, 16 hrs @ RT

Specification	SAE J1756	Results	Status
70 Units min		86	Pass

SECTION: 3.2.3 Flammability

3.2.3 Burn Rate, Component

Specification	ISO 3795* / SAE J369*	Results	Status
< 100 mm / min		< B 25	Pass

SECTION 3.2.4 Resistance to Mildew

3.2.4 7 Days @ 38°C / 98% RH

Specification	FLTM BO 131-03*	Results	Status
No Visible Mildew Growth or Objectionable Odor		No Offensive Odor or Evidence of Mildew	Pass

SECTION 3.2.5 Accelerated Weathering Resistance

3.2.5 2250 Hours, ISO 105-A-02 AATCC Eval 1

Specification	ASTM D7869*	Results	Status
Rating 4 Min		Not Tested	Not Tested

SECTION: 3.2.6 Adhesion Strength

3.2.6.1 Original Bond Strength

3.2.6.2 After Heat Ageing Change, 168 hrs @ 100°C

3.2.6.3 After Environmental Cycling Change, 10 Cycles
4 hrs @ 100°C
4 hrs @ 38°C / 95% RH
16 hrs @ -30°C

Specification	ASTM D1000	Results	Status
0.48 N / mm	0.85	TEAR	Pass
- 25% max	0.86	TEAR	Pass
- 25% max	0.90	TEAR	Pass
No Cracking, Delamination or Crazing			

SECTION: 3.2.6 Adhesion Strength

3.2.6.1 Original Bond Strength

3.2.6.2 After Heat Ageing Change, 168 hrs @ 100°C

3.2.6.3 After Environmental Cycling Change, 10 Cycles
4 hrs @ 100°C
4 hrs @ -30°C
16 hrs @ -30°C

Specification	ASTM D1000	Results	Status
No Cracking, Delamination or Crazing	Good, Stable, No Defects or Lifting		Pass
	Good, Stable, No Defects or Lifting		Pass
	Good, Stable, No Defects or Lifting		Pass

SECTION 3.2.8 Stress Cracking Test for Plastics

3.2.8 Stress Cracking Test for Plastics

Specification	ASTM D1000	Results	Status
No Cracking or Crazing	Not Tested		Not Tested

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.