



250 Chester Street
Painesville, Ohio 44077
Phone: **866-GO-AVERY (866-462-8379)**
Fax: **888-358-4469**
email: **psa.tape@averydennison.com**
URL: **tapes.averydennison.com**

TEST REPORT

SAMPLE: **FT 1126**
SUPPORT: **XLPE FOAM**
SUBSTRATE: **ABS**
CERT NO.: **221214 - 0903**



GMW 14444-CODE-3

OEM Rev Date: 0

Material Related Interior Part Performance
CODE 3 Position Within Vehicle is Not Exposed to Direct Sunlight
C - All Parts In Contact With Customer Feet, e.g. Floor Mat, Door Trim Mechanically

TAPE REQUIREMENTS:

SECTION: **4.3 Flammability**

Initial, Component

GMW3232

Specification

< 100 mm / min

Results

< B 25

Status

Pass

SECTION: **4.4.6 Scratch Resistance**

100 Cycles CS-10, 500 g Load

Specification

No Wear Thru to Fabric Backing

Results

Not Applicable

Status

Not Applicable

SECTION: **4.5.1 Odor**

Wet Condition, Coding A - 24 hrs @ 70°C, Deionized Water

GMW 3205

Specification

> 4 Rating

Results

8 Noticeable, Trace

Status

Pass

Dry Condition, Coding B - 24 hrs @ 70°C

> 4 Rating

7 Clearly Noticeable, But Not Objectionable

Pass

High Temp Condition - 24 hrs @ 105°C

> 4 Rating

6 Tolerable

Pass

SECTION: **4.5.1 Emission Testing**

Fogging, 3 hrs @ 100°C, 21°C Cooling, Post 60 mins @ RT

GMW 3235

Specification

> 60 %

Results

86.2

Status

Pass

SECTION: **4.5.2 Impact Resistance**

After 4 hrs @ -30°C

GMW 14093 CODE 3, Apparatus A

Specification

**No Breakage, Cracks or Separation
from 2 - 2.5 J Impacts**

Results

No Separation or Cracks

Status

Pass

4.5.6 Adhesive Requirements of Pressure Sensitive Adhesive, Mechanically Retained Bonded Items

TEST: **Adhesion**

As Received

GMW 14892

Specification

350 N / m

Results

499.6

Mode

ADHEREND

Status

Adherend-Pass

Humidity - GMW 14729 Option A, 144 hrs @ 38°C / 100% RH

350 N / m

401.6

ADHEREND

Adherend-Pass

Oven Aged, 24 hrs @ 85°C, < 60s

350 N / m

210.7

ADHEREND

Adherend-Pass

Environmental Cycles 2(x), GMW 14124 Cycle M

350 N / m

409.2

ADHEREND

Adherend-Pass

CERTIFIED BY:


Jake Cowdick, Automotive Application Specialist

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.