



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 1966
SUPPORT: EPDM RUBBER
SUBSTRATE: PAINTED METAL
CERT NO.: 221215 - 1305

GMW 16443 TYPE-I

OEM Rev Date: Dec 10

Adhesion Performance Requirements For Adhesive Backed Foam
Type I - An adhesive backed foam composite that is entrapped and/or
mechanically retained for the life of the vehicle



TAPE REQUIREMENTS:

3.5.1 Type I Exposure

SECTION 3.3 Edge Adhesion

3.5.3, Initial, As Received

	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.5.3, Initial, As Received	Securely Bonded	Stable, No Lifting or Removal	Pass

3.5.4, Heat Aged, ISO 188, 168 hrs @ 80C

3.5.4, Heat Aged, ISO 188, 168 hrs @ 80C	Securely Bonded	Stable, No Lifting or Removal	Pass
--	-----------------	-------------------------------	------

3.5.5, Humidity, GMW 14729 Option B, 168 hrs @ 40°C / 100% RH

3.5.5, Humidity, GMW 14729 Option B, 168 hrs @ 40°C / 100% RH	Securely Bonded	Stable, No Lifting or Removal	Pass
---	-----------------	-------------------------------	------

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.