250 Chester Street
Painesville, Ohio 44077
Phone: **866-GO-AVERY (866-462-8379)**
Fax: **888-358-4469**
email: **psa.tape@averydennison.com**
URL: **tapes.averydennison.com**

TEST REPORT

PRODUCT: **FT 7770X**
SUPPORT: PEU FOAM
SUBSTRATE: ABS
CERT NO.: 221215 - 1306

GMW 16443 TYPE-I
OEM Rev Date: Oct 16
Adhesion Performance Requirements For Adhesive Backed Light Trim and Foam

Type I - An adhesive backed foam composite that is entrapped and/or mechanically retained for the life of the vehicle

TAPE REQUIREMENTS:

3.5.1 Type I Exposure

SECTION **3.3** **Edge Adhesion**	**Specification**	**Results**	**Status**
3.5.3, Initial, As Received	**Securely Bonded**	Stable, No Lifting or Removal	**Pass**
3.5.4, Heat Aged, ISO 188 07, 168 hrs @ 80ºC	**Securely Bonded**	Stable, No Lifting or Removal	**Pass**
3.5.5, Humidity, GMW 14729 10 Option B, 168 hrs @ 40ºC / 100% RH	**Securely Bonded**	Stable, No Lifting or Removal	**Pass**

CERTIFIED BY: Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.