



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FBD 8970 12 PT BD
SUPPORT: LOW PERM FOAM
SUBSTRATE: PAINTED METAL
STD CERT NO.: 221215 - 1327

GMW 16443 TYPE-I

OEM Rev Date: Dec 10

Adhesion Performance Requirements For Adhesive Backed Foam
TYPE I - An adhesive backed foam composite that is entrapped
and/or mechanically retained for the life of the vehicle

GMW 3221 Code A - 50% RH (+/- 5%)



TAPE REQUIREMENTS:

3.5.1 TYPE I Exposure

SECTION 3.3 Edge Adhesion

3.53, Initial, As Received

Specification

Securely Bonded

Results

Stable, No Lifting or Removal

Status

Pass

3.54, Heat Aged, ISO 188 07, 168 hrs @ 80C

Securely Bonded

Stable, No Lifting or Removal

Pass

3.55, Humidity, GMW 14729 10 Option A, 168 hrs @ 38°C / 100% RH

Securely Bonded

Stable, No Lifting or Removal

Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.