



250 Chester Street  
Painesville, Ohio 44077  
Phone: 866-GO-AVERY (866-462-8379)  
Fax: 888-358-4469  
email: psa.tape@averydennison.com  
URL: tapes.averydennison.com

PRODUCT: FBR 1950  
SUPPORT: PORON FOAM  
SUBSTRATE: PC ABS  
CERT NO.: 221215 - 1432



### GMW 16443-TYPE-II-EXTERIOR-CYCLE-C

OEM Rev Date: Aug 18

Adhesion Performance Requirements For Adhesive Backed Light Trim and Foam  
Type II - An adhesive backed foam composite that is retained by the adhesive for the life of the vehicle

Passing Type II Meets and Exceeds 3.5.1 Type I Exposure Requirements

#### TAPE REQUIREMENTS:

##### 3.5.2 TYPE-II Exposure

###### SECTION 3.3.3 Edge Adhesion

3.5.3, Initial, As Received - 24 hrs @ RT

3.5.4, Heat Aged 168 hrs @ 80°C per ISO 188

3.5.5, After Humidity 168 hrs @ 38°C / 100% RH per GMW 14729 Option A

3.5.6, Cycle Exposure, GMW 14124, 2x Cycle C

17 hrs @ -30°C

72 hrs @ 70°C

24 hrs @ 38°C / 100% RH

7 hrs @ -30°C

24 hrs @ 38°C / 100% RH

7 hrs @ 70°C

24 hrs @ 38°C / 100% RH

3.5.8, Cold Shock, 72 hrs @ 54°C, 4 hrs @ -30°C

###### SECTION 3.4 Peel Adhesion

3.5.3, Initial, As Received - 24 hrs @ RT

ISO 8510-2

3.5.4, Heat Aged 168 hrs @ 80°C per ISO 188

3.5.5, After Humidity 168 hrs @ 38°C / 100% RH per GMW 14729 Option A

3.5.6, Cycle Exposure, GMW 14124, 2x Cycle C

17 hrs @ -30°C

72 hrs @ 70°C

24 hrs @ 38°C / 100% RH

7 hrs @ -30°C

24 hrs @ 38°C / 100% RH

7 hrs @ 70°C

3.5.8, Cold Shock, 72 hrs @ 54°C, 4 hrs @ -30°C

###### SECTION 3.5.8 Cold Shock

3.5.8, Cold Shock, 72 hrs @ 54°C, 4 hrs @ -30°C

###### SECTION: 3.7.1 Release Liner

3.7.2, Liner Removal @ RT

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.

## Appendix A Table A2

PRODUCT: **FBR 1950**  
 SUPPORT: **PORON FOAM**  
 SUBSTRATE: **PC ABS**  
 CERT NO.: **221215 - 1432**

Table A2: GMW16443 Type II Applications Test Data Form

Section	Test	Standard	Requirements	Sample	Visual Edge Adhesion	Peel N/m	Failure Mode					
3.5.3	Initial, As Received - 24 hrs @ RT	ISO 8510-2	Minimum of 525 N/m and Cohesive Failure of One or Both of the Adherends	1	Stable, No Lifting or Removal	800.3	CF					
				2	Stable, No Lifting or Removal	705.8	CF					
				3	Stable, No Lifting or Removal	467.6	CF					
	Heat Aged 168 hrs @ 80°C per ISO 188			1	Stable, No Lifting or Removal	616.4	CF					
				2	Stable, No Lifting or Removal	591.9	CF					
				3	Stable, No Lifting or Removal	789.8	CF					
	After Humidity 168 hrs @ 38°C / 100% RH per GMW 14729 Option A			1	Stable, No Lifting or Removal	443.1	CF					
				2	Stable, No Lifting or Removal	458.8	CF					
				3	Stable, No Lifting or Removal	469.3	CF					
	Cycle Exposure, GMW 14124, 2x Cycle C			1	Stable, No Lifting or Removal	711.0	CF					
				2	Stable, No Lifting or Removal	579.7	CF					
				3	Stable, No Lifting or Removal	726.8	CF					
	Cold Shock, 72 hrs @ 54°C, 4 hrs @ -30°C			1								
				2								
				3								
3.5.8				1	Stable, No Lifting or Removal	537.6	CF					
				2	Stable, No Lifting or Removal	544.6	CF					
				3	Stable, No Lifting or Removal	618.2	CF					

Section	Test	Standard	Requirements	Sample	Result
3.6	Tape Wet Out, GMW15851	GMW 15851 is restricted and we cannot purchase	85% Tape Wet Out	1	Not Tested
				2	Not Tested
				3	Not Tested
3.7.1	Release Liner Contact	To Be Determined @ Tier	No Lift Prior To Vehicle Install	1	TBD
				2	TBD
				3	TBD
3.7.2	Liner Removal	ISO 8510-2	Less Than Or Equal To 65 N/m	1	12.3
				2	17.5
				3	17.5