



250 Chester Street  
Painesville, Ohio 44077  
Phone: 866-GO-AVERY (866-462-8379)  
Fax: 888-358-4469  
email: psa.tape@averydennison.com  
URL: tapes.averydennison.com

## TEST REPORT

PRODUCT: FT 8392 12 PT BD  
SUPPORT: PVC FOAM  
SUBSTRATE: 20% TALC PP  
CERT NO.: 221215 - 1445



### GMW 16443-TYPE-II-EXTERIOR-CYCLE-C

OEM Rev Date: Aug 18

Adhesion Performance Requirements For Adhesive Backed Light Trim and Foam  
Type II - An adhesive backed foam composite that is retained by the adhesive for the life of the vehicle

Passing Type II Meets and Exceeds 3.5.1 Type I Exposure Requirements

#### TAPE REQUIREMENTS:

##### 3.5.2 TYPE-II Exposure

###### SECTION 3.3.3 Edge Adhesion

3.5.3, Initial, As Received - 24 hrs @ RT

3.5.4, Heat Aged 168 hrs @ 80°C per ISO 188

3.5.5, Humidity 168 hrs @ 38°C / 100% RH per GMW 14729 Option A

3.5.6, Cycle Exposure, GMW 14124, 2x Cycle C

17 hrs @ -30°C

72 hrs @ 70°C

24 hrs @ 38°C / 100% RH

7 hrs @ -30°C

24 hrs @ 38°C / 100% RH

7 hrs @ 70°C

24 hrs @ 38°C / 100% RH

3.5.8, Cold Shock, 72 hrs @ 54°C, 4 hrs @ -30°C

###### SECTION 3.4 Peel Adhesion

ISO 8510-2

3.5.3, Initial, As Received - 24 hrs @ RT

3.5.4, Heat Aged 168 hrs @ 80°C per ISO 188

3.5.5, Humidity 168 hrs @ 38°C / 100% RH per GMW 14729 Option A

3.5.6, Cycle Exposure, GMW 14124, 2x Cycle C

17 hrs @ -30°C

72 hrs @ 70°C

24 hrs @ 38°C / 100% RH

7 hrs @ -30°C

24 hrs @ 38°C / 100% RH

7 hrs @ 70°C

3.5.8, Cold Shock, 72 hrs @ 54°C, 4 hrs @ -30°C

###### SECTION 3.5.8 Cold Shock

3.5.8, Cold Shock, 72 hrs @ 54°C, 4 hrs @ -30°C

###### SECTION: 3.7.1 Release Liner

3.7.2, Liner Removal @ RT

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.5.3, Initial, As Received - 24 hrs @ RT	Securely Bonded	Stable, No Lifting or Removal	Pass

	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.5.4, Heat Aged 168 hrs @ 80°C per ISO 188	Securely Bonded	Stable, No Lifting or Removal	Pass

	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.5.5, Humidity 168 hrs @ 38°C / 100% RH per GMW 14729 Option A	Securely Bonded	Stable, No Lifting or Removal	Pass

	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.5.6, Cycle Exposure, GMW 14124, 2x Cycle C	Securely Bonded	Stable, No Lifting or Removal	Pass

	<u>Specification</u>	<u>Results</u>	<u>Status</u>
17 hrs @ -30°C	Securely Bonded	Stable, No Lifting or Removal	Pass

	<u>Specification</u>	<u>Results</u>	<u>Status</u>
72 hrs @ 70°C	Securely Bonded	Stable, No Lifting or Removal	Pass

	<u>Specification</u>	<u>Results</u>	<u>Status</u>
24 hrs @ 38°C / 100% RH	Securely Bonded	Stable, No Lifting or Removal	Pass

	<u>Specification</u>	<u>Results</u>	<u>Status</u>
7 hrs @ -30°C	Securely Bonded	Stable, No Lifting or Removal	Pass

	<u>Specification</u>	<u>Results</u>	<u>Status</u>
24 hrs @ 38°C / 100% RH	Securely Bonded	Stable, No Lifting or Removal	Pass

	<u>Specification</u>	<u>Results</u>	<u>Status</u>
24 hrs @ 38°C / 100% RH	Securely Bonded	Stable, No Lifting or Removal	Pass

	<u>Specification</u>	<u>Results</u>	<u>Status</u>
7 hrs @ 70°C	Securely Bonded	Stable, No Lifting or Removal	Pass

	<u>Specification</u>	<u>Results</u>	<u>Status</u>
24 hrs @ 38°C / 100% RH	Securely Bonded	Stable, No Lifting or Removal	Pass

	<u>Specification</u>	<u>Results</u>	<u>Status</u>
7 hrs @ -30°C	Securely Bonded	Stable, No Lifting or Removal	Pass

	<u>Specification</u>	<u>Results</u>	<u>Status</u>
24 hrs @ 38°C / 100% RH	Securely Bonded	Stable, No Lifting or Removal	Pass

	<u>Specification</u>	<u>Results</u>	<u>Status</u>
24 hrs @ 38°C / 100% RH	Securely Bonded	Stable, No Lifting or Removal	Pass

	<u>Specification</u>	<u>Results</u>	<u>Status</u>
7 hrs @ 70°C	Securely Bonded	Stable, No Lifting or Removal	Pass

	<u>Specification</u>	<u>Results</u>	<u>Status</u>
24 hrs @ 38°C / 100% RH	Securely Bonded	Stable, No Lifting or Removal	Pass

	<u>Specification</u>	<u>Results</u>	<u>Status</u>
7 hrs @ -30°C	Securely Bonded	Stable, No Lifting or Removal	Pass

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.

## Appendix A Table A2

PRODUCT: **FT 8392 12 PT BD**  
 SUPPORT: **PVC FOAM**  
 SUBSTRATE: **20% TALC PP**  
 CERT NO.: **221215 - 1445**

Table A2: GMW16443 Type II Applications Test Data Form

Section	Test	Standard	Requirements	Sample	Visual Edge Adhesion	Peel N/m	Failure Mode
3.5.3	Initial, As Received - 24 hrs @ RT	ISO 8510-2	Minimum of 525 N/m and Cohesive Failure of One or Both of the Adherends	1	Stable, No Lifting or Removal	457.1	AF-P
				2	Stable, No Lifting or Removal	711.0	AF-P
				3	Stable, No Lifting or Removal	513.1	AF-P
3.5.4	Heat Aged 168 hrs @ 80°C per ISO 188	ISO 8510-2	Minimum of 525 N/m and Cohesive Failure of One or Both of the Adherends	1	Stable, No Lifting or Removal	1288.9	AF-P
				2	Stable, No Lifting or Removal	1218.9	AF-P
				3	Stable, No Lifting or Removal	1206.6	AF-P
3.5.5	Humidity 168 hrs @ 38°C / 100% RH per GMW 14729 Option A	ISO 8510-2	Minimum of 525 N/m and Cohesive Failure of One or Both of the Adherends	1	Stable, No Lifting or Removal	901.9	AF-P
				2	Stable, No Lifting or Removal	1066.5	AF-P
				3	Stable, No Lifting or Removal	957.9	AF-P
3.5.6	Cycle Exposure, GMW 14124, 2x Cycle C	ISO 8510-2	Minimum of 525 N/m and Cohesive Failure of One or Both of the Adherends	1	Stable, No Lifting or Removal	1036.8	AF-P
				2	Stable, No Lifting or Removal	1106.8	AF-P
				3	Stable, No Lifting or Removal	1175.1	AF-P
		ISO 8510-2	Minimum of 525 N/m and Cohesive Failure of One or Both of the Adherends	1			
				2			
				3			
3.5.8	Cold Shock, 72 hrs @ 54°C, 4 hrs @ -30°C	ISO 8510-2	Minimum of 525 N/m and Cohesive Failure of One or Both of the Adherends	1	Stable, No Lifting or Removal	1113.8	AF-P
				2	Stable, No Lifting or Removal	1178.6	AF-P
				3	Stable, No Lifting or Removal	1126.1	AF-P

Section	Test	Standard	Requirements	Sample	Result
3.6	Tape Wet Out, GMW15851	GMW 15851 is restricted and we cannot purchase	85% Tape Wet Out	1	Not Tested
				2	Not Tested
				3	Not Tested
3.7.1	Release Liner Contact	To Be Determined @ Tier	No Lift Prior To Vehicle Install	1	TBD
				2	TBD
				3	TBD
3.7.2	Liner Removal	ISO 8510-2	Less Than Or Equal To 65 N/m	1	10.5
				2	19.3
				3	14.0