



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: stus.averydennison.com

TEST REPORT

PRODUCT: FT 1149X 12 PT BD
SUPPORT: FLOCK
SUBSTRATE: ABS
STD CERT NO.: 221215 - 1457



GMW 16875 TYPE IA-CYCLE-D

OEM Rev Date: Jan 13

Performance Requirements of Anti-Squeak, Itch, Rattle Fiber Tape

Type IA material is a flocked fabric or felt tape coated with a permanent acrylic PSA not exposed to UV Initial

TAPE REQUIREMENTS:

SECTION: Liner Removal Initial RT	ISO 8510-2	<u>Specification</u> 900 N / m	<u>Results</u> 23.3	<u>Status</u> Pass
SECTION: Peel Adhesion Aged, 72 hrs @ RT	ISO 8510-2	<u>Specification</u> 350 N / m	<u>Results</u> 1664.6	<u>Status</u> Pass
Humidity, 24 hrs @ 38°C / 95% RH		350 N / m	1736.4	Pass
Aged, 168 hrs @ 70°C		350 N / m	1273.0	Pass
GMW 14124 CYCLE D 24 hrs @ 38°C / 100% RH 4 hrs @ 85°C 3 hrs @ RT 17 hrs @ 85°C 168 hrs @ 70°C 4 hrs @ -30C 100 hrs @ 70°C		350 N / m	1326.7	Pass
SECTION: Shear Strength, MD 4 hrs @ -18°C	ASTM D1000	<u>Specification</u> 7500 N / m	<u>Results</u> 14672.8	<u>Status</u> Pass
24 hrs @ 60°C		3500 N / m	5332.4	Pass
SECTION: Taber Abrasion* 500 Cycles CS-10, 1 kg Load	GMW3208	<u>Specification</u> No Wear Thru to Fabric Backing	<u>Results</u> Worn But Not Thru	<u>Status</u> Pass
SECTION: Flammability Initial, Component	GMW3232	<u>Specification</u> 100 mm / min	<u>Results</u> < B 25	<u>Status</u> Pass
SECTION: Xenon Weatherometer* Not Applicable	GMW14162	<u>Specification</u> No Degradation, Stiffening, Bleaching or Objectionable Color	<u>Results</u> Not Applicable	<u>Status</u> NA
SECTION: Odor* Wet Condition, Coding A - 24 hrs @ 70°C, Deionized Water Dry Condition, Coding B - 24 hrs @ 70°C High Temp Condition - 24 hrs @ 105°C	GMW3205	<u>Specification</u> 6 Min Rating	<u>Results</u> 9 Just Noticeable 9 Just Noticeable 9 Just Noticeable	<u>Status</u> Pass Pass Pass
SECTION: VOC* Per GMW 16853	GMW15634	<u>Specification</u> 6 mg	<u>Results</u> Not Tested	<u>Status</u> NA
SECTION: Gravimetric Fogging Initial, Component	GMW3235 Method B - HAAKE	<u>Specification</u> 2 mg	<u>Results</u> 0.958	<u>Status</u> Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.