



250 Chester Street  
Painesville, Ohio 44077  
Phone: 866-GO-AVERY (866-462-8379)  
Fax: 888-358-4469  
email: psa.tape@averydennison.com  
URL: stus.averydennison.com

## TEST REPORT

PRODUCT: FT 1126  
SUPPORT: 0.5 MM FELT  
SUBSTRATE: PP  
STD CERT NO.: 221216 - 0929

### GMW 16875 TYPE II-CYCLE-D

OEM Rev Date: Jan 13

Performance Requirements of Anti-Squeak, Itch, Rattle Fiber Tape  
Type II material is a nonwoven tape coated with a permanent acrylic PSA  
Initial



#### TAPE REQUIREMENTS:

SECTION:	TEST	Specification	Results	Status
SECTION: <b>Liner Removal</b>	ISO 8510-2 Initial RT	<b>900 N / m</b>	17.5	<b>Pass</b>
SECTION: <b>Peel Adhesion</b>	ISO 8510-2 Aged, 72 hrs @ RT	<b>280 N / m</b>	1462.1	<b>Pass</b>
Humidity, 24 hrs @ 38°C / 95% RH		<b>280 N / m</b>	1592.8	<b>Pass</b>
Aged, 168 hrs @ 70°C		<b>280 N / m</b>	1417.1	<b>Pass</b>
GMW 14124 CYCLE D		<b>280 N / m</b>	1528.6	<b>Pass</b>
24 hrs @ 38°C / 100% RH 4 hrs @ 85°C 3 hrs @ RT 17 hrs @ 85°C 168 hrs @ 70°C 4 hrs @ -30C 100 hrs @ 70°C				
SECTION: <b>Shear Strength, MD</b>	ASTM D1000 4 hrs @ -18°C	<b>2500 N / m</b>	3654.9	<b>Pass</b>
24 hrs @ 60°C		<b>2500 N / m</b>	1868.9	<b>Pass</b>
SECTION: <b>Taber Abrasion*</b>	GMW3208 500 Cycles CS-10,0.5 kg Load	<b>Specification</b> <b>No Wear Thru to Fabric Backing</b>	<b>Results</b> Worn But Not Thru	<b>Pass</b>
SECTION: <b>Flammability</b>	GMW3232 Initial, Component	<b>Specification</b> <b>100 mm / min</b>	<b>Results</b> < B 25	<b>Pass</b>
SECTION: <b>Xenon Weatherometer*</b>	GMW14162 Not Applicable	<b>Specification</b> <b>No Degradation, Stiffening, Bleaching or Objectionable Color</b>	<b>Results</b> Not Applicable	<b>NA</b>
SECTION: <b>Odor*</b>	GMW3205 Wet Condition, Coding A - 24 hrs @ 70°C, Deionized Water Dry Condition, Coding B - 24 hrs @ 70°C High Temp Condition - 24 hrs @ 105°C	<b>Specification</b> <b>6 Min Rating</b>	<b>Results</b> 8 Noticeable, Trace 7 Clearly Noticeable, But Not Objectionable 7 Clearly Noticeable, But Not Objectionable	<b>Pass</b> <b>Pass</b> <b>Pass</b>
SECTION: <b>VOC*</b>	GMW15634 Per GMW 16853	<b>Specification</b> <b>6 mg</b>	<b>Results</b> Not Tested	<b>NA</b>
SECTION: <b>Gravimetric Fogging</b>	GMW3235 Method B 18 hrs @ 100°C, 21°C Cooling, 24 hr RT Desiccant	<b>Specification</b> <b>2 mg</b>	<b>Results</b> 1.26	<b>Pass</b>

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.