



250 Chester Street  
Painesville, Ohio 44077  
Phone: 866-GO-AVERY (866-462-8379)  
Fax: 888-358-4469  
email: psa.tape@averydennison.com  
URL: tapes.averydennison.com

## TEST REPORT

PRODUCT: BNW 5SB1K028LV  
SUPPORT: FELT  
SUBSTRATE: ABS  
STD CERT NO.: 240725 - 0724



### GMW 16875 TYPE II-CYCLE-D

OEM Rev Date: Oct 18

Performance Requirements of Anti-Squeak, Itch, Rattle Fiber Tape  
Type II material is a nonwoven tape coated with a permanent acrylic PSA  
Initial

#### TAPE REQUIREMENTS:

SECTION: <b>Liner Removal</b> Initial RT	ISO 8510-2	<u>Specification</u> <b>900 N / m</b>	<u>Results</u> 7.7	<u>Status</u> <b>Pass</b>
SECTION: <b>Peel Adhesion</b> Aged, 72 hrs @ RT	ISO 8510-2	<u>Specification</u> <b>280 N / m</b>	<u>Results</u> 1388.7	<u>Status</u> <b>Pass</b>
Humidity, 24 hrs @ 38°C / 95% RH		<b>280 N / m</b>	1765.2	<b>Pass</b>
Aged, 168 hrs @ 70°C		<b>280 N / m</b>	2545.2	<b>Pass</b>
GMW 14124 CYCLE D 24 hrs @ 38°C / 100% RH 4 hrs @ 85°C 3 hrs @ RT 17 hrs @ 85°C 168 hrs @ 70°C 4 hrs @ -30C 100 hrs @ 70°C		<b>280 N / m</b>	2483.8	<b>Pass</b>
SECTION: <b>Shear Strength, MD</b> 4 hrs @ -18°C	ASTM D1000	<u>Specification</u> <b>2500 N / m</b>	<u>Results</u> 3926.3	<u>Status</u> <b>Pass</b>
24 hrs @ 60°C		<b>2500 N / m</b>	3251.7	<b>Pass</b>
SECTION: <b>Taber Abrasion*</b> 500 Cycles CS-10,0.5 kg Load	GMW3208	<u>Specification</u> <b>No Wear Thru to Fabric Backing</b>	<u>Results</u> Not Tested	<u>Status</u> <b>Not Tested</b>
SECTION: <b>Flammability</b> Initial, Component	GMW3232	<u>Specification</u> <b>100 mm / min</b>	<u>Results</u> < B 25	<u>Status</u> <b>Pass</b>
SECTION: <b>Xenon Weatherometer*</b> Not Applicable	GMW14162	<u>Specification</u> <b>No Degradation, Stiffening, Bleaching or Objectionable Color</b>	<u>Results</u> Not Applicable	<u>Status</u> <b>NA</b>
SECTION: <b>Odor*</b> Wet Condition, Coding A - 24 hrs @ 70°C, Deionized Water Dry Condition, Coding B - 24 hrs @ 70°C High Temp Condition - 24 hrs @ 105°C	GMW3205	<u>Specification</u> <b>6 Min Rating</b>	<u>Results</u> Not Tested Not Tested Not Tested	<u>Status</u> <b>Not Tested</b> <b>Not Tested</b> <b>Not Tested</b>
SECTION: <b>VOC*</b> Per GMW 16853	GMW15634	<u>Specification</u> <b>6 mg</b>	<u>Results</u> Not Tested	<u>Status</u> <b>NA</b>
SECTION: <b>Gravimetric Fogging</b> 18 hrs @ 100°C, 21°C Cooling, 24 hr RT Desiccant	GMW3235 Method B	<u>Specification</u> <b>&lt; 2 mg</b>	<u>Results</u> 1.3	<u>Status</u> <b>Pass</b>

CERTIFIED BY:

David Nichols II, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.