



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT F3315AZ
SUPPORT: 1.0mil FELT
SUBSTRATE: ABS
STD CERT NO.: 260218 - 0727



GMW 16875 TYPE II-CYCLE-D
OEM Rev Date: Oct 18
Performance Requirements of Anti-Squeak, Itch, Rattle Fiber Tape
Type II material is a nonwoven tape coated with a permanent acrylic PSA
Initial

TAPE REQUIREMENTS:

| SECTION: | Standard | Specification | Results | Status |
|--|------------------|---|--|---|
| SECTION: Liner Removal Initial RT | ISO 8510-2 | 900 N / m | 9.9 | Pass |
| SECTION: Peel Adhesion Aged, 72 hrs @ RT | ISO 8510-2 | 280 N / m | 1139.1 | Pass |
| Humidity, 24 hrs @ 38°C / 95% RH | | 280 N / m | 1635.3 | Pass |
| Aged, 168 hrs @ 70°C | | 280 N / m | 1708.6 | Pass |
| GMW 14124 CYCLE D 24 hrs @ 38°C / 100% RH 4 hrs @ 85°C 3 hrs @ RT 17 hrs @ 85°C 168 hrs @ 70°C 4 hrs @ -30C 100 hrs @ 70°C | | 280 N / m | 1700.2 | Pass |
| SECTION: Shear Strength, MD 4 hrs @ -18°C | ASTM D1000 | 2500 N / m | 7909.7 | Pass |
| 24 hrs @ 60°C | | 2500 N / m | 4188.7 | Pass |
| SECTION: Taber Abrasion 500 Cycles CS-10,0.5 kg Load | GMW3208 | No Wear Thru to Fabric Backing | Worn But Not Thru | Pass |
| SECTION: Flammability Initial, Component | GMW3232 | 100 mm / min | < B 25 | Pass |
| SECTION: Xenon Weatherometer* Not Applicable | GMW14162 | No Degradation, Stiffening, Bleaching or Objectionable Color | Not Applicable | NA |
| SECTION: Odor* Wet Condition, Coding A - 24 hrs @ 70°C, Deionized Water Dry Condition, Coding B - 24 hrs @ 70°C High Temp Condition - 24 hrs @ 105°C | GMW3205 | 6 Min Rating | Not Tested Not Tested Not Tested | Not Tested Not Tested Not Tested |
| SECTION: VOC* Per GMW 16853 | GMW15634 | 6 mg | Not Tested | NA |
| SECTION: Gravimetric Fogging 18 hrs @ 100°C, 21°C Cooling, 24 hr RT Desiccant | GMW3235 Method B | < 2 mg | 0.0 | Pass |

CERTIFIED BY:
David Nichols II, Automotive Lab Technician

ISSUE DATE: 1-1-26

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.