



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: HPA 1905
SUPPORT: PRIMED EPDM
SUBSTRATE: PAINTED METAL A
CERT NO.: 221221 - 1257



HONDA 1752Z-SH3-0000
OEM Rev Date: Aug 89
Tank Band Cushion

TAPE REQUIREMENTS:

SECTION: 6-1 Adhesion Properties
6-1-3, Normal Condition

Specification
0.14 mPa (kg / cm2)

Results
0.178

Status
Pass

6-1-4, After Immersion, 24 hr @ 20°C, None

0.14 mPa (kg / cm2)

0.201

Pass

6-1-5, After Heat Aging, 70 hrs @ 100°C

0.14 mPa (kg / cm2)

0.362

Pass

CERTIFIED BY:


Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.