



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: stus.averydennison.com

TEST REPORT

PRODUCT: FT 8392
SUPPORT: FELT
SUBSTRATE: PAINTED ABS
STD CERT NO.: 221221 - 1301

HYUNDAI MS 711-12 Type A1

OEM Rev Date: Jan 03

Decorative Sheets (Pressure Sensitive Adhesive Baked Bonding Type) - Interior Trims
Ordinary tape for general use laminated on a resin sheet such as an ABS resin sheet, used in general purpose



TAPE REQUIREMENTS:

SECTION:	Peeling Strength	MS 300-33*	Specification	Results	Status
4.4	Normal State Adhesion, 20 mins @ RT		1.0 kg / 25mm	1.8	Pass
4.5	Oven Aging, 168 hrs @ 80°C		1.0 kg / 25mm	3.0	Pass
4.6	Heat Cycle, 1x 3 hrs @ 80°C 1 hr @ 20°C 3 hrs @ -30°C 1 hr @ 20°C 15 hrs @ 40°C / 95% RH 1 hr @ 20°C		1.0 kg / 25mm	2.0	Pass
4.15	Humidity, 168 hrs @ 40°C / 95% RH		1.0 kg / 25mm	2.1	Pass

SECTION:	Appearance	MS 300-33*	Specification	Results	Status
4.5	Oven Aging, 168 hrs @ 80°C		No Discoloring, Peeling, Creasing, Etc.	Stable, No Discoloring, Creasing or Peeling	Pass
4.6	Heat Cycle, 1x		No Discoloring, Peeling, Creasing, Etc.	Stable, No Discoloring, Creasing or Peeling	Pass
4.15	Humidity, 168 hrs @ 40°C / 95% RH		No Discoloring, Peeling, Creasing, Etc.	Stable, No Discoloring, Creasing or Peeling	Pass

SECTION:	Staining, Swelling	MS 300-33*	Specification	Results	Status
4.5	Oven Aging, 168 hrs @ 80°C		No Staining or Swelling On Applicable Materials	No Staining, Lifting or Removal	Pass
4.6	Heat Cycle, 1x		No Staining or Swelling On Applicable Materials	No Staining, Lifting or Removal	Pass
4.15	Humidity, 168 hrs @ 40°C / 95% RH		No Staining or Swelling On Applicable Materials	No Staining, Lifting or Removal	Pass

SECTION:	Creep	MS 300-33*	Specification	Results	Status
4.16	Creep Resistance, Immersed 168 hrs @ 60°C		No Staining, Blistering or Appearance Changes	No Blistering Defects or Appearance Changes	Pass
4.16	Creep Resistance, Immersed 168 hrs @ 60°C		0.5 kg / 25mm	1.3	Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.