



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 8728
SUPPORT: ALUMINUM FOIL
SUBSTRATE: PAPER BOARD
CERT NO.: 221221 - 1301



HYUNDAI MS 711-12 Type A1

OEM Rev Date: Dec 94

Decorative Sheets (Pressure Sensitive Adhesive Baked Bonding Type) - Interior Trims
A1 - Ordinary tape for general use laminated on a resin sheet such as an ABS resin sheet, used in general purpose

TAPE REQUIREMENTS:

SECTION: Peeling Strength

4.4 Normal State Adhesion, 20 mins @ RT

	4.4	Specification	Results	Status
		1.0 kg / 25 mm	2.7	Pass

4.5 Oven Aging, 168 hrs @ 80°C

1.0 kg / 25 mm

4.4

Pass

4.6 Heat Cycle, 1x

1.0 kg / 25 mm

3.4

Pass

3 hrs @ 80°C
1 hr @ 20°C
3 hrs @ -30°C
1 hr @ 20°C
15 hrs @ 40°C / 95% RH
1 hr @ 20°C

4.15 Humidity, 168 hrs @ 40°C / 95% RH

1.0 kg / 25 mm

1.7

Pass

SECTION: Appearance

4.5 Oven Aging, 168 hrs @ 80°C

Specification

No Discoloring, Peeling, Creasing, Etc.

Results

Stable, No Discoloring, Creasing or Peeling

Status

Pass

4.6 Heat Cycle, 1x

Stable, No Discoloring, Creasing or Peeling

Pass

4.15 Humidity, 168 hrs @ 40°C / 95% RH

Stable, No Discoloring, Creasing or Peeling

Pass

SECTION: Staining, Swelling

4.5 Oven Aging, 168 hrs @ 80°C

Specification

No Staining or Swelling On Applicable Materials

Results

No Staining, Lifting or Removal

Status

Pass

4.6 Heat Cycle, 1x

No Staining, Lifting or Removal

Pass

4.15 Humidity, 168 hrs @ 40°C / 95% RH

No Staining, Lifting or Removal

Pass

SECTION: Creep

4.16 Creep Resistance, 3 hrs @ 80°C

Specification

No Staining, Blistering or Appearance Changes

Results

No Blistering Defects or Appearance Changes

Status

Pass

4.16 Creep Resistance, 3 hrs @ 80°C

0.5 kg / 25mm

3.5

Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.