



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 5832
SUPPORT: ALUMINUM FOIL
SUBSTRATE: PAPER BOARD
CERT NO.: 221221 - 1302



HYUNDAI MS 711-12 Type A2

OEM Rev Date: Jan 03

Decorative Sheets (Pressure Sensitive Adhesive Baked Bonding Type) - Interior Trims

A2 - Ordinary tape for general use laminated on a metallic sheet such as an aluminum sheet, used in general purpose

TAPE REQUIREMENTS:

SECTION:	Spec	Specification	Results	Status
SECTION: Shear Strength	4.4	3.0 kg / cm²	3.0	Pass
4.4 Normal State Adhesion, 20 mins @ RT				
4.5 Oven Aging, 168 hrs @ 80°C		3.0 kg / cm²	3.6	Pass
4.6 Heat Cycle, 1x		2.5 kg / cm²	3.2	Pass
		3 hrs @ 80°C 1 hr @ 20°C 3 hrs @ -30°C 1 hr @ 20°C 15 hrs @ 40°C / 95% RH 1 hr @ 20°C		
4.15 Humidity, 168 hrs @ 40°C / 95% RH		2.5 kg / cm²	3.1	Pass
SECTION: Appearance	4.6	No Discoloring, Peeling, Creasing, Etc.	Results Stable, No Discoloring, Creasing or Peeling	Status Pass
4.5 Oven Aging, 168 hrs @ 80°C				
4.6 Heat Cycle, 1x			Stable, No Discoloring, Creasing or Peeling	Pass
4.15 Humidity, 168 hrs @ 40°C / 95% RH			Stable, No Discoloring, Creasing or Peeling	Pass
SECTION: Staining, Swelling	4.15	Specification No Staining or Swelling On Applicable Materials	Results No Staining, Lifting or Removal	Status Pass
4.5 Oven Aging, 168 hrs @ 80°C				
4.6 Heat Cycle, 1x			No Staining, Lifting or Removal	Pass
4.15 Humidity, 168 hrs @ 40°C / 95% RH			No Staining, Lifting or Removal	Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.