



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 1126 12 PT BD
SUPPORT: ISOSEAL FOAM
SUBSTRATE: PAINTED METAL
CERT NO.: 221221 - 1309



INTEVA MX650011 Type III

OEM Rev Date: Mar 08

Adhesion Performance Requirements of Pressure Sensitive Adhesive Coated Parts (Minimal Stress)
Type III

5.3 For a part bonded at a Tier 1 supplier and mechanically fastened on line
adhesion:

Passing Type III Meets and Exceeds Type I and II Requirements

TAPE REQUIREMENTS:

4. REQUIREMENTS

SECTION 4.3.1 Creep Resistance

4.3.1, A Initial, Bonded @ 25°C, 50% RH - 7 Days @ 40°C

Specification
No Lifting or Shifting

Results
Stable, No Lifting or Removal

Status
Pass

SECTION 4.3.2 Peel Adhesion

4.3.2, A Bonded @ 25°C, 50% RH - 20 mins @ RT

Specification
350 N / m

Results
921.2

Status
Pass

SECTION 4.3.3 Impact

4.3.3, A Bonded @ 25°C, 50% RH, - 20 mins @ RT

Specification
No Separation from 2 Impacts

Results
No Impact Separation

Status
Pass

SECTION 4.3.4 Edge Adhesion

4.3.4, A Bonded @ 25°C, 50% RH - 20 mins @ RT

Specification
Securely Bonded

Results
Stable, No Lifting or Removal

Status
Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.