



250 Chester Street  
Painesville, Ohio 44077  
Phone: 866-GO-AVERY (866-462-8379)  
Fax: 888-358-4469  
email: psa.tape@averydennison.com  
URL: tapes.averydennison.com

**TEST REPORT**  
PRODUCT: FT 1126  
SUPPORT: ISOSEAL FOAM  
SUBSTRATE: PAINTED METAL  
CERT NO.: 221221 - 1309



**INTEVA MX650011 Type III**

OEM Rev Date: Mar 08

Adhesion Performance Requirements of Pressure Sensitive Adhesive Coated Parts (Minimal Stress)  
Type III

5.3 For a part bonded at a Tier 1 supplier and mechanically fastened on line  
adhesion:

Passing Type III Meets and Exceeds Type I and II Requirements

**TAPE REQUIREMENTS:**

**4. REQUIREMENTS**

**SECTION 4.3.1 Creep Resistance**

4.3.1, A Initial, Bonded @ 25°C, 50% RH - 7 Days @ 40°C

Specification  
No Lifting or Shifting

Results  
Stable, No Lifting or Removal

Status  
Pass

**SECTION 4.3.2 Peel Adhesion**

4.3.2, A Bonded @ 25°C, 50% RH - 20 mins @ RT

Specification  
350 N / m

Results  
921.2

Status  
Pass

**SECTION 4.3.3 Impact**

4.3.3, A Bonded @ 25°C, 50% RH, - 20 mins @ RT

Specification  
No Separation from 2 Impacts

Results  
No Impact Separation

Status  
Pass

**SECTION 4.3.4 Edge Adhesion**

4.3.4, A Bonded @ 25°C, 50% RH - 20 mins @ RT

Specification  
Securely Bonded

Results  
Stable, No Lifting or Removal

Status  
Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.