



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 8392 12 PT BD
SUPPORT: PVC FOAM
SUBSTRATE: LEXAN
CERT NO.: 221221 - 1310



INTEVA MX650011 Type III

OEM Rev Date: Mar 08

Adhesion Performance Requirements of Pressure Sensitive Adhesive Coated Parts (Minimal Stress)
Type III

5.3 For a part bonded at a Tier 1 supplier and mechanically fastened on line
adhesion:

Passing Type III Meets and Exceeds Type I and II Requirements

TAPE REQUIREMENTS:

4. REQUIREMENTS

SECTION 4.3.1 Creep Resistance

4.3.1, A Initial, Bonded @ 25°C, 50% RH - 7 Days @ 40°C

Specification

No Lifting or Shifting

Results

Stable, No Lifting or Removal

Status

Pass

SECTION 4.3.2 Peel Adhesion

4.3.2, A Bonded @ 25°C, 50% RH - 20 mins @ RT

Specification

350 N / m

Results

1558.0

Status

Pass

SECTION 4.3.3 Impact

4.3.3, A Bonded @ 25°C, 50% RH, - 20 mins @ RT

Specification

No Separation from 2 Impacts

Results

No Impact Separation

Status

Pass

SECTION 4.3.4 Edge Adhesion

4.3.4, A Bonded @ 25°C, 50% RH - 20 mins @ RT

Specification

Securely Bonded

Results

Stable, No Lifting or Removal

Status

Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.