



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 8327 12 PT BD
SUPPORT: EPDM SBR FOAM
SUBSTRATE: E-COATED METAL
CERT NO.: 221221 - 1459



TOYOTA TSK 6505G - 2A2
OEM Rev Date: Mar 96
Toyota Engineering Standard - Caulking, Sponge, Sealants
2A2 - Semi-close cell type synthetic rubber (Soft)
Rubber Based

TAPE REQUIREMENTS:

SECTION: **4.11.1 Peel Adhesion (T-Peel Adhesion)**

4.11.1, Initial, 5 mins As Received

Specification
Cohesive Failure

ASTM D1876

Results
Cohesive Split

Status
Pass

SECTION: **4.11.2 Peel Adhesion**

4.11.2, Peel Adhesion, Initial, 5 mins As Received

Specification
11.8 N / 15 mm

ASTM D3330

Results
15.1

Status
Pass

4.11.2, Peel Adhesion, 24 hrs @ RT

11.8 N / 15 mm

14.8

Pass

4.11.2, Peel Adhesion, High Temp, 24 hrs @ 80°C

11.8 N / 15 mm

21.3

Pass


4.11.2, Peel Adhesion, Water Immersed, 10 days @ 40°C, 1 hr @ RT

11.8 N / 15 mm

16.2

Pass

CERTIFIED BY:


Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.