



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT B
SUPPORT: EPDM SBR FOAM
SUBSTRATE: E-COATED METAL
CERT NO.: 221221 - 1500

TOYOTA TSK 6505G - 2B2

OEM Rev Date: Mar 96
Toyota Engineering Standard - Caulking, Sponge, Sealants
2B2 - Semi-close cell type synthetic rubber (Hard)
Rubber Based



TAPE REQUIREMENTS:

SECTION: **4.11.1 Peel Adhesion (T-Peel Adhesion)**

4.11.1, Initial, 5 mins As Received

<u>Specification</u>	ASTM D1876	<u>Results</u>	<u>Status</u>
Cohesive Failure		Cohesive Split	Pass

SECTION: **4.11.2 Peel Adhesion**

4.11.2, Peel Adhesion, Initial, 5 mins As Received

<u>Specification</u>	ASTM D3330	<u>Results</u>	<u>Status</u>
10.8 N / 15 mm		18.4	Pass

4.11.2, Peel Adhesion, 24 hrs @ RT

10.8 N / 15 mm	18.8	Pass
-----------------------	------	-------------

4.11.2, Peel Adhesion, High Temp, 24 hrs @ 80°C

10.8 N / 15 mm	16.6	Pass
-----------------------	------	-------------

4.11.2, Peel Adhesion, Water Immersed, 10 days @ 40°C, 1 hr @ RT

10.8 N / 15 mm	18.4	Pass
-----------------------	------	-------------

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.