



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: **FT 8346**
SUPPORT: **5 MM XLPE FOAM**
SUBSTRATES: **ALUMINUM**
CERT NO.: 221222 - 0743

VALEO PDT NVC 00001-C

Rev Date: Apr 11


Plastic Foam Seals - Material Specification



TEST PARAMETERS:

SECTION:		<u>Specification</u>	<u>Results</u>	<u>Status</u>
SECTION: Flammability	Initial, Component	FMVSS 302 < 100 mm / min	< B 25	Pass
SECTION: Odor	Dry Condition - Coding B, 24 hrs @ 70°C	GMW 3205 B > 6 Rating	7 Clearly Noticeable, But Not Objectionable	Pass
SECTION: Fogging, Oil Bath - Gravimetric	18 hrs @ 90°C, 21°C Cooling, Post 24 hrs @ RT	GMW 3235 Method B > 2 mg	0.2	Pass
SECTION: Mildew	Component, 14 days @ 40°C	GMW 3259 No Typical Mildew Odor and or Mildew Growth	No Objectional Odor or Presence of Mildew	Pass
SECTION: Aging Test 3	Initial	Specification No Adhesion Loss or Lift	Good, Stable, No Lifting	Pass
	48 hrs @ 23°C / 50% RH		Good, Stable, No Lifting	Pass
Thermal Shock - 5 Cycles	24 hrs @ -40°C 24 hrs @ 90°C / 95% RH 24 hrs @ 23°C / 50% RH		Good, Stable, No Lifting	Pass
SECTION: Aging Test 3	Initial	Specification 0.2 daN/cm	0.38	Pass
	48 hrs @ 23°C / 50% RH	0.3 daN/cm	0.70	Pass
Thermal Shock - 5 Cycles	24 hrs @ -40°C 24 hrs @ 90°C / 95% RH 24 hrs @ 23°C / 50% RH 24 hrs @ 23°C / 50% RH	0.3 daN/cm	0.82	Pass

CERTIFIED BY:



Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.