



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: **FBA 8960**
SUPPORT: **24 45 RAF DARK GRAY POLYURETHANE FOAM**
SUBSTRATES: **ALUMINUM**
CERT NO.: **221222 - 0745**

VALEO PDT NVC 00001-C
Rev Date: Apr 11
Plastic Foam Seals - Material Specification



TEST PARAMETERS:

SECTION:	TEST	SPECIFICATION	RESULTS	STATUS
SECTION: Flammability Initial, Component	FMVSS 302	< 100 mm / min	SE	Pass
SECTION: Odor 1 hr @ 80°C, Cool to 60°C, Test	NVX 15 012 Rev B*	3 Max Rating	1 Weak Odor	Pass
SECTION: Fogging, Oil Bath - Photometric 3 hrs @ 100°C, 21°C Cooling, Post 1 hr @ RT	GMW 3235 Method A	> 85 %	100	Pass
3 hrs @ 100°C, 21°C Cooling, Post 16 hrs @ RT		> 85 %	100	Pass
SECTION: Fogging, Oil Bath - Gravimetric 18 hrs @ 90°C, 21°C Cooling, 24 hr RT Desiccant	GMW 3235 Method B	< 4 mg	0.63	Pass
SECTION: Aging Test 3 Initial		Specification No Adhesion Loss or Lift	Good, Stable, No Lifting	Pass
48 hrs @ 23°C / 50% RH			Good, Stable, No Lifting	Pass
Thermal Shock - 5 Cycles			Good, Stable, No Lifting	Pass
	24 hrs @ -40°C			
	24 hrs @ 90°C / 95% RH			
	24 hrs @ 23°C / 50% RH			
SECTION: Aging Test 3 Initial	ISO-8510-2	0.2 daN/cm	0.58	Pass
48 hrs @ 23°C / 50% RH		0.3 daN/cm	0.91	Pass
Thermal Shock - 5 Cycles		0.3 daN/cm	1.03	Pass
	24 hrs @ -40°C			
	24 hrs @ 90°C / 95% RH			
	24 hrs @ 23°C / 50% RH			
	24 hrs @ 23°C / 50% RH			

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.