



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FBA 8960
SUPPORT: 5 MM XLPE FOAM
SUBSTRATES: ALUMINUM
CERT NO.: 221222 - 0743

VALEO PDT NVC 00001-C

Rev Date: Apr 11

Plastic Foam Seals - Material Specification



TEST PARAMETERS:

SECTION:	TEST	Specification	Results	Status
SECTION: Flammability	FMVSS 302	< 100 mm / min	< B 25	Pass
Initial, Component				
SECTION: Odor	GMW 3205 B	> 6 Rating	7 Clearly Noticeable, But Not Objectionable	Pass
Dry Condition - Coding B, 24 hrs @ 70°C				
SECTION: Fogging, Oil Bath - Gravimetric	GMW 3235 Method B	< 2 mg	0.3	Pass
18 hrs @ 90°C, 21°C Cooling, Post 24 hrs @ RT				
SECTION: Mildew	GMW 3259	No Typical Mildew Odor and or Mildew Growth	No Objectional Odor or Presence of Mildew	Pass
Component, 14 days @ 40°C				
SECTION: Aging Test 3		Specification	Results	Status
Initial		No Adhesion Loss or Lift	Good, Stable, No Lifting	Pass
48 hrs @ 23°C / 50% RH			Good, Stable, No Lifting	Pass
Thermal Shock - 5 Cycles			Good, Stable, No Lifting	Pass
24 hrs @ -40°C				
24 hrs @ 90°C / 95% RH				
24 hrs @ 23°C / 50% RH				
SECTION: Aging Test 3	ISO 8510-2	Specification	Results	Status
Initial		0.2 daN/cm	0.24	Pass
48 hrs @ 23°C / 50% RH		0.3 daN/cm	0.43	Pass
Thermal Shock - 5 Cycles		0.3 daN/cm	0.38	Pass
24 hrs @ -40°C				
24 hrs @ 90°C / 95% RH				
24 hrs @ 23°C / 50% RH				
24 hrs @ 23°C / 50% RH				

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-25

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.