



250 Chester Street  
Painesville, Ohio 44077  
Phone: **866-GO-AVERY (866-462-8379)**  
Fax: **888-358-4469**  
email: **psa.tape@averydennison.com**  
URL: **tapes.averydennison.com**

## TEST REPORT

PRODUCT: **FBA 8960**  
SUPPORT: **POLYURETHANE FOAM**  
SUBSTRATES: **ALUMINUM**  
CERT NO.: **221222 - 0745**



**VALEO PDT NVC 00001-C**  
Rev Date: Apr 11  
Plastic Foam Seals - Material Specification

### TEST PARAMETERS:

SECTION: <b>Flammability</b> Initial, Component	FMVSS 302	<u>Specification</u> <b>&lt; 100 mm / min</b>	<u>Results</u> SE	<u>Status</u> <b>Pass</b>
SECTION: <b>Odor</b> 1 hr @ 80°C, Cool to 60°C, Test	NVX 15 012 Rev B*	<u>Specification</u> <b>3 Max Rating</b>	<u>Results</u> 1 Weak Odor	<u>Status</u> <b>Pass</b>
SECTION: <b>Fogging, Oil Bath - Photometric</b> 3 hrs @ 100°C, 21°C Cooling, Post 1 hr @ RT	GMW 3235 Method A	<u>Specification</u> <b>&gt; 85 %</b>	<u>Results</u> 100	<u>Status</u> <b>Pass</b>
3 hrs @ 100°C, 21°C Cooling, Post 16 hrs @ RT		<b>&gt; 85 %</b>	100	<b>Pass</b>
SECTION: <b>Fogging, Oil Bath - Gravimetric</b> 18 hrs @ 90°C, 21°C Cooling, 24 hr RT Desiccant	GMW 3235 Method B	<u>Specification</u> <b>&lt; 4 mg</b>	<u>Results</u> 0.63	<u>Status</u> <b>Pass</b>
SECTION: <b>Aging Test 3</b> Initial		<u>Specification</u> <b>No Adhesion Loss or Lift</b>	<u>Results</u> Good, Stable, No Lifting	<u>Status</u> <b>Pass</b>
48 hrs @ 23°C / 50% RH			Good, Stable, No Lifting	<b>Pass</b>
Thermal Shock - 5 Cycles			Good, Stable, No Lifting	<b>Pass</b>
24 hrs @ -40°C				
24 hrs @ 90°C / 95% RH				
24 hrs @ 23°C / 50% RH				
SECTION: <b>Aging Test 3</b> Initial	ISO-8510-2	<u>Specification</u> <b>0.2 daN/cm</b>	<u>Results</u> 0.58	<u>Status</u> <b>Pass</b>
48 hrs @ 23°C / 50% RH		<b>0.3 daN/cm</b>	0.91	<b>Pass</b>
Thermal Shock - 5 Cycles		<b>0.3 daN/cm</b>	1.03	<b>Pass</b>
24 hrs @ -40°C				
24 hrs @ 90°C / 95% RH				
24 hrs @ 23°C / 50% RH				
24 hrs @ 23°C / 50% RH				

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: **1-1-25**

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.