



AFB™ 8640GS


Avery Dennison AFB™ 8640GS is a grey acrylic foam tape. This product has excellent adhesion and shear strength, and also resists UV lights and elevated temperatures. AFB™ 8640GS is suitable for badge and emblem mounting in automobiles.

FEATURES:

- Foam tape with viscoelastic acrylic foam carrier
- Closed cell structure
- Acrylic adhesive system
- Polypropylene liner helps provide good moisture stability and easier converting with its high tear strength

BENEFITS:

- High adhesion combined with good shear absorbs shock and distributes stress evenly
- Good high temperature resistance
- High bond strength to irregular or curved surfaces
- Very good holding power



CONSTRUCTION:

Liner:

Red Polypropylene Liner

Adhesive:

Acrylic

Carrier:

Gray Acrylic Foam Core

Adhesive:

Acrylic

AFB™ 8640GS

| Adhesive Properties: | | Typical Values | | |
|----------------------|-------------|----------------|------|---------------|
| Thickness | ASTM D-3652 | US Mils | MM's | Micron's (µm) |
| Liner: | | 3.2 | 0.08 | 81 |
| Carrier & Adhesive: | | 15.8 | 0.40 | 401 |
| Total Caliper: | | 19.0 | 0.48 | 483 |

PEEL ADHESION Test Method(s): PSTC-101, ASTM D-3330

Aluminum Foil 90° 12 in /min (305 mm / min)

| Substrate | | Lbf / In | N / 100 mm |
|---------------------------|-------------|----------|------------|
| Automotive MSE Clear Coat | 24 hr dwell | 7.4 | 130 |
| | | | |
| | | | |

Aluminum Foil 90° 12 in /min (305 mm / min)

| | | | |
|---------------------------|-------------|-----|----|
| Automotive MSE Clear Coat | 24 hr dwell | 3.4 | 60 |
| | | | |
| | | | |

DYNAMIC SHEAR Test Method(s): ASTM D-1002

Aluminum Foil 0.5 in /min (12.7 mm / min)

| Substrate | | Lbf / In ² | kPa |
|-----------|-------------|-----------------------|-----|
| Liner | 24 hr dwell | 58.0 | 400 |
| | | | |
| | | | |

NORMAL TENSILE Test Method(s): ASTM D-897Aluminum 2 in / min (50.8 mm / min) 1" sq (6.5 cm²)

| Substrate | | Lbf / In ² | kPa |
|-----------|-------------|-----------------------|-----|
| Aluminum | 24 hr dwell | 58.0 | 400 |
| | | | |
| | | | |

STATIC SHEAR Test Method(s): PSTC-101, ASTM D-3330Aluminum Foil 1" sq (6.5 cm²) 1000 g @ Room Temp

| Substrate | | Min to Fail | |
|-----------|-------------|-------------|--|
| SS | 24 hr dwell | > 10,000 | |
| | | | |
| | | | |

Aluminum Foil 1" sq (6.5 cm²) 500 g @ 80°C

| | | | |
|----|-------------|----------|--|
| SS | 24 hr dwell | > 10,000 | |
| | | | |
| | | | |

TEMPERATURES

| | ° F | ° C |
|------------------------------|---------|---------|
| Long Term Temp (10,000 mins) | 248 ° F | 120 ° C |
| Short Term Temp (240 mins) | 320 ° F | 160 ° C |

THE LISTED VALUES ARE TYPICAL AND NOT INTENDED TO SERVE AS PRODUCT SPECIFICATIONS

APPLICATION TECHNIQUES

- It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied be clean, dry, and free of grease or oil
- Bond strength is dependent upon the amount of adhesive-to-surface contact developed
- Note that different pressure, time and temperature on different (film / rigid) surface achieves different performance

STORAGE / SHELF LIFE

- One year when stored at 64-72°F (18-22°C) / 30-70% relative humidity, out of direct sunlight and in original packaging.

Please refer to Tapes.AveryDennison.com for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2015 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation. All other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation.

Performance
Tapes

Asia Pacific
Kunshan, China,
NO. 618 Nanhe Road
Kunshan Economic &
Technological Zone
China, 215335
Phone: +86 512 57155001
Fax: +86 512 57155059

Europe
Tieblokkenlaan 1
B-2300 Turnhout
Belgium
Phone: +32 (0)14 40 48 11
Fax: +32 (0)14 40 48 55

North America
250 Chester Street
Painesville, Ohio
44077 USA
Phone: +1 866-462-8379
Fax: +1 888-358-4469