
FT 7366

FEATURES:

- · Modified acrylic adhesive
- Remoisturised liner
- · Clear polyester carrier

BENEFITS:

- Offers high temperature and UV resistance
- Good adhesion to a lot of surfaces, also low energy surfaces
- High degree of transparency
- Good moisture and dimensional stability
- Very good handling and conversion (die-cutting) characteristics



CONSTRUCTION:

Liner:

Yellow Glassine

Adhesive 1 Liner:

Acrylic

Carrier:

Polyester

Adhesive 2 Uwind:

Acrylic

FT 7366

FT 7366						
Adhesive Properties:		Typical Values US Mils MM's				
Thickness		Test Method(s): PSTC-133	2.9		MM's	
Liner: Carrier and Adhesives:			5.9		0.07 0.15	
Carrier and Adriesives.			5.5		0.13	
Total Caliper:			8.8		0.22	
PEEL ADHESION		Test Method(s): PSTC-101, A	STM D-3330, STD-10			
	' min					
Substrate	1		Lbf / In	US Oz / In	N / Meter	
SS	Liner	20 min dwell	5.6	90	981	
		24 hr dwell	5.9	95	1040	
Polypropylene	Liner	20 min dwell	3.6	58	630	
отургоругене	LITICI	20 11111 011011	0.0			
		24 hr dwell	5.0	80	879	
TENSILE		Test Method(s): PSTC-131, A	STM D-882, STD-3A,B,C			
Product 180°			Lbf / In	110 0= /15	N / Meter	
Substrate Product	Liner		8.6	US Oz / In 137	1501	
ELONGATION Product 180°		Test Method(s): PSTC-131, A	STM D-882, STD-3A,B,C			
Substrate			%			
Product	Liner		40			
LOOP TACK		Test Method(s): PSTC-16, ST	D-7			
	' / min					
Substrate			Lbf / In	US Oz / In	N / Meter	
SS	Liner	Initial	9.1	146	1600	
STATIC SHEAR		Toot Mothod(a): DCTC 407 A	CTM D 2654 CTD 0			
2 mil PET 1" sq (6.5 d	cm2) 1000 g	Test Method(s): PSTC-107, A	3 TIVI D 3034, 3 LD-9			
Substrate			Min to Fail			
SS	Liner		> 8,000			
TEMPERATURES			° F		° C	
Min Application Temp			50 ° F		10 ° C	
Max Continuous Operating Temp			212 º F		100 ° C	
Max Intermittent Operating Temp			248 ° F		120 ° C	

THE LISTED VALUES ARE TYPICAL AND NOT INTENDED TO SERVE AS PRODUCT SPECIFICATIONS

APPLICATION TECHNIQUES

- It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied be clean, dry, and free of grease or oil
- Bond strength is dependent upon the amount of adhesive-to-surface contact developed
- · Note that different pressure, time and temperature on different (film / rigid) surface achieves different performance

STORAGE / SHELF LIFE

• Two years when stored at 64-72°F (18-22°C) / 30-70% relative humidity, out of direct sunlight and in original packaging.

Please refer to Tapes. Avery Dennison.com for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2013 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation. Avery™ and all other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation.



Performance

South America Rua Francisco Foga, 225 250 Chester Street 13280-000 Vinhedo

SP Brazil

Fax: +55 19 3876 7682

North America Painesville, Ohio 44077 USA

Fax: +1 888-358-4469