



FT 7387


Fastape[™] 7387 is manufactured with a differential removable acrylic and permanent rubber adhesive system. Designed for polishing pad applications

FEATURES:

- High tack rubber based adhesive
- Excellent removable acrylic adhesive providing good creep resistance and clean removability.

BENEFITS:

- · Easy release liner
- Improved die-cutting characteristics
- Matrix strippable
- Reinforces the polishing material



CONSTRUCTION:

Liner:
Glassine
Adhesive 1 Liner:
Removable Acrylic
Carrier:
Polyester
Adhesive 2 Uwind:
Permanent Rubber



Performance Tapes

Adhesive Properties:		Typical Values			
Thickness		Test Method(s): PSTC-133	US Mils		MM's
_iner:			3.2		0.08
Adhesive 1 Liner:			1.4		0.04
Carrier:			0.5		0.01
Adhesive 2 Uwind:			1.4		0.04
Total Caliper:		6.5		0.17	
PEEL ADHESION		Test Method(s): PSTC-101, ASTM	1 D-3330, STD-10		
2 mil PET 180º 12" Substrate	min		Lbf / In	US Oz / In	N / Meter
SS	Liner	Initial	2.7	43	473
	LINGI	initia	2.1	01	017
	Unwind	Initial	6.7	107	1173
Painted Steel	Liner	Initial	2.5	39	430
	Unwind	Initial	14.3	229	2501
	Griwind		0.71	LLŪ	2001
Polycarbonate	Liner	Initial	2.8	45	490
		la de l	45.0	0.40	0000
	Unwind	Initial	15.0	240	2626
PP	Liner	Initial	0.8	13	140
		1.50.1	10.0	000	0000
	Unwind	Initial	13.0	209	2283
LOOP TACK		Test Method(s): PSTC-16, STD-7			•
2 mil PET 20" min					
Substrate			Lbf / In	US Oz / In	N / Meter
SS	Liner	Initial	3.1	49	540
	Unwind	Initial	10.3	166	1811
STATIC SHEAR		Test Method(s): PSTC-107, ASTN	1 D 3654, STD-9		
2 mil PET 1" sq (6.5 c	m2) 1000 g				
Substrate			Min to Fail		
SS	Liner	Initial	> 1,000		
	Unwind	Initial	> 10,000		
TEMPERATURES			° F		° C
Min Application Temp			50 ° F		10 ° C
Max Continuous Operating Temp			131 º F	1	55 º C
Max Intermittent Operating Temp		158 º F		70 º C	

THE LISTED VALUES ARE TYPICAL AND NOT INTENDED TO SERVE AS PRODUCT SPECIFICATIONS

APPLICATION TECHNIQUES

• It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied be clean, dry, and free of grease or oil

• Bond strength is dependent upon the amount of adhesive-to-surface contact developed

· Note that different pressure, time and temperature on different (film / rigid) surface achieves different performance

STORAGE / SHELF LIFE

• Two years when stored at 64-72°F (18-22°C) / 30-70% relative humidity, out of direct sunlight and in original packaging.

Please refer to Tapes.AveryDennison.com for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2013 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation. Avery™ and all other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation.



Performance

Tapes

Asia Pacific Kunshan, China, NO. 618 Nanhe Road Kunshan Economic & Technological Zone China, 215335 Phone: +86 512 57155001 Fax: +86 512 57155059

Europe Tieblokkenlaan 1 B-2300 Turnhout Belaium Fax: +32 (0)14 40 48 55

South America Rua Francisco Foga, 225 250 Chester Street 13280-000 Vinhedo SP Brazil Phone: +32 (0)14 40 48 11 Phone: +55 19 3876 7736 Phone: +1 866-462-8379 Fax: +55 19 3876 7682 Fax: +1 888-358-4469

North America Painesville, Ohio 44077 USA