



FT 5262DL

Avery Dennison FT 5262DL is a dual liner, 60 micron double coated black polyester tape with a modified acrylic adhesive designed for light blocking in applications where high temperature resistance and high adhesion are required. Used for bonding back light units such as reflectors, light guide plates, diffusion sheets and brightness enhancement films into LCD display modules. FT 5262 DL is a differential tape, one side for permanent bonding; the other side is for temporary bonding.

FEATURES:

- Modified acrylic adhesives
- High opacity black PET carrier
- Dual PET liners

BENEFITS:

- Provides high temperature resistance and a strong, lasting bond to a variety of materials
- Differential tape, one side strong permanent bonding especially design for small size device, and the other side is for easy re-work handling
- Optimal bonding strength and easy handling performance for use with small components
- Offers excellent light shielding in back light unit (BLU) applications - 0.3% light transmission by ASTM D 1003 without pin hole
- Reduces risk of wrinkle, shrinkage, fiber and particle contamination in clean room conditions



CONSTRUCTION:

Liner 1:

Polyester

Adhesive:

Removable modified acrylic

Carrier:

Black Polyester

Adhesive:

Modified acrylic

Liner 2:

Polyester

FT 5262DL

Adhesive Properties	Typical Values		
	US Mils	mm	Microns (µm)
THICKNESS			
Liner 1	1.95	0.05	50
Adhesive + Carrier	2.34	0.06	60
Liner 2	1.17	0.03	30
Total	5.46	0.14	140

*PSTC-133

PEEL ADHESION

2 mil PET; 180°; 12" / min

Substrate		Lbf / in		N / 25mm	
		20 min	24 hr	20 min	24 hr
Stainless steel	Permanent side	3.4	3.7	15	16.25
	Temporary side	1.7	2.0	7.5	8.75
Polycarbonate	Permanent side	4.0	4.9	17.5	21.25
	Temporary side	2.0	2.6	8.75	11.25

*PSTC-101, ASTM D-3330, STD-10

LOOP TACK

2 mil PET; 90°; 20" / min; 1" sq (6.5 cm²)

Substrate		Lbf / in	N / 25mm
Glass	Permanent side	4.9	21.25
	Temporary side	2.0	8.75

*PSTC-16, STD-7

STATIC SHEAR

Foil; 1" sq (6.5 cm²); 1000 g

Min to Fail

>10,000

*PSTC-107, ASTM D 3654, STD-9

TEMPERATURES

Min. Application Temp.	50 ° F	10 ° C
Max. Continuous Operating Temp.	212 ° F	100 ° C
Max. Intermittent Operating Temp.	248 ° F	120 ° C

*TEST METHODS

Note: The listed values are typical only and not intended to serve as product specifications

APPLICATION TECHNIQUES

- It is essential with all pressure-sensitive tapes the application surface is clean, dry and free of grease and oil
- Bond strength is dependent upon the amount of adhesive-to-surface contact developed
- Note that different pressure, time and temperature on different (firm / rigid) surface achieves different performance

STORAGE AND SHELF LIFE

The shelf life of the product is two years when stored at 18-22°C / 64-72°F, 30-70% relative humidity and out of direct sunlight, in original packaging.

Please refer to Tapes.AveryDennison.com for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2016 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation. All other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation.



Performance
Tapes

Asia Pacific
Kunshan, China,
NO. 618 Nanhe Road
Kunshan Economic &
Technological Zone
China, 215335
Phone: +86 512 57155001
Fax: +86 512 57155059

Europe
Tieblokkenlaan 1
B-2300 Turnhout
Belgium
Phone: +32 (0)14 40 48 11
Fax: +32 (0)14 40 48 55

North America
250 Chester Street
Painesville, Ohio
44077 USA
Phone: +1 866-462-8379
Fax: +1 888-358-4469

For more information on our bonding tapes and adhesive solutions, visit Tapes.AveryDennison.com