




FM M1702

FM M1702 is part of a pressure-sensitive fastening system consisting of a variety of cross linked, closed-cell, polyethylene foams in various thicknesses, densities and colors, and coated both sides with specifically formulated pressure-sensitive adhesives.

CONSTRUCTION & TYPICAL APPLICATION:

- Consists of a 0,8 mm white, cross-linked, closed-cell, polyethylene foam coated on both sides with a rubber based adhesive. It offers very high peel and shear properties.
- Produced in self-wound format on a calendered paper liner.
- For applications where high shear and high performance are required: e.g. hooks, cable clips, sky domes, hangers, rear view mirrors.
- White Goods Industry: door handle bonding, holding wires and cable clips, mounting shelf support clips.
- Automotive industry: The mounting of the number plates onto car bodies.



- Siliconised white paper
- Side 2: Rubber based adhesive
- White PE Foam 0,8mm
- Side 1: Rubber based adhesive

Adhesion with Substrates

Metal / Aluminium	High	Acrylic / PET	High
Glass / Ceramics	High	Polystyrene	High
Painted Surface	High	PP / PE / PS	High
Wood / Board / Paper	High	Textile / Cotton	High
Soft PVC	Low	Rubber / EPDM	High
Rigid PVC	High	Smooth Substrate	High
PC / ABS	High	Rough Substrate	High

RESISTANCE:

- Resistant to water, detergents and alcohol. Low resistance to plasticizers and low outdoor resistance. Not recommended for use in contact with aliphatic or aromatic hydrocarbons.

SHELF LIFE:

- 2 years when stored at 15/25° C and \pm 50% relative humidity.

ADDITIONAL INFORMATION:

- IMDS – automotive registration: FM M1702 has been introduced in the IMDS (International Material Data System).

FM M1702

ADHESIVE DATA	Typical Values*	Test Method
Peel 180° (N/25mm) on brushed stainless steel (ref. Nokoro 304 poli. N°4) - after 20 minutes	> 15**	FTM 1
Shear on brushed stainless steel (ref. Nokoro 304 poli. N°4) 1kg – 25mm x 25mm (hours)	> 5000	FTM 8

CARRIER DATA	Typical Values*	Test Method
Tensile (N/15mm)	MD 16 CD 12	DIN 53455
Elongation (%) (max.)	MD 500 CD 500	DIN 53455
Density	High	

TEMPERATURE RESISTANCE	Typical Values*	Test Method
Minimum Application Temperature	+ 10°C	
End-use Temperature Range	- 40°C to + 60°C	

RELEASE LINER	Typical Values*	Test Method
White Silicone Paper	90 gr/sqm	ISO 536

THICKNESS	Typical Values*	Test Method
Carrier + Adhesive	0,9mm	ISO 534

*Values given are typical and are not necessarily for use in specifications.

APPLICATION TECHNIQUES:

- It is essential with all pressure-sensitive tapes the application surface is clean, dry and free of grease and oil
- Bond strength is dependent upon the amount of adhesive-to-surface contact developed
- Note that different pressure, time and temperature on different (firm / rigid) surface achieves different performance

IMPORTANT NOTICE:

Information on the above characteristics is based upon tests we believe to be reliable. The values given are typical values that vary according to application conditions. The values are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine prior to use the suitability of this material for their specific purposes. All Avery Dennison materials described herein are sold subject to Avery Dennison Conditions of Sales, a copy of which is available upon request.

Please refer to [Tapes.AveryDennison.com](https://www.tapes.averydennison.com) for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2017 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation. All other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation.



Asia Pacific
Kunshan, China,
No. 618 Nanhe Road
Kunshan Economic &
Technological Zone
China 215335
Phone: +86 512 57155001
Fax: +86 512 57155059

Europe
Tieblokkenlaan 1
B-2300 Turnhout
Belgium
Phone: +32 (0)14 40 48 11
Fax: +32 (0)14 40 48 55

Bld J.F. Kennedy 1
7060 Soignies
Belgium
Phone: +32 (0)14 404 963
Fax: +32 (0)14 40 48 55

North America
250 Chester Street
Painesville, Ohio
44077 USA
Phone: +1 866-462-8379
Fax: +1 888-358-4469

For more information on our bonding tapes and adhesive solutions,
visit [Tapes.AveryDennison.com](https://www.tapes.averydennison.com)