




# FT F2001

**FT F2001** is part of a transfer or unsupported pressure sensitive adhesive system for assembling purposes. The adhesives used are acrylic polymer or synthetic rubber based formulations. FT F2001 is protected by one or two silicone coated release liners.

## CONSTRUCTION & TYPICAL APPLICATION:

- Free film of solvent based pure acrylic adhesive protected on one side with a 95 gr kraft paper liner and on the other side with a 100  $\mu$  clear polyethylene film.
- Has medium tack and peel properties, and high shear resistance.
- For applications where high clarity is required: e.g. acrylic signs, taxi & car number plates, passports, etc.



## Adhesion with Substrates

|                      |        |                  |        |
|----------------------|--------|------------------|--------|
| Metal / Aluminium    | Medium | Acrylic / PET    | Medium |
| Glass / Ceramics     | Medium | Polystyrene      | Medium |
| Painted Surface      | Medium | PP / PE / PS     | Medium |
| Wood / Board / Paper | Medium | Textile / Cotton | Medium |
| Soft PVC             | Medium | Rubber / EPDM    | Medium |
| Rigid PVC            | Medium | Smooth Substrate | Medium |
| PC / ABS             | Medium | Rough Substrate  | Medium |

## RESISTANCE:

- Resistant to water, detergents, alcohol, aliphatic and some aromatic hydrocarbons. Medium resistance to plasticizers and high outdoor resistance. Not recommended for use in contact with ketones, esters or chlorinated hydrocarbons.

## SHELF LIFE:

- 2 years when stored at 15/25° C and  $\pm$  50% relative humidity.

## ADDITIONAL INFORMATION:

- Skin contact approval: The adhesive of FT F2001 has been lab tested and its Primary Irritation Index (P.I.I.) was calculated to be 0,1, « negligible irritating » in accordance with the criteria of ECETOC.
- Automotive approval: British Standard : BS AU145D.

## FT F2001

| ADHESIVE DATA  | Typical Values* | Test Method    |
|--|-----------------|----------------|
| <b>Quick Tack</b> (N/25mm) on brushed stainless steel (ref. Nokoro 304 poli. N°4)  | 11              | FTM 9          |
| <b>Peel 180°</b> (N/25mm) on brushed stainless steel (ref. Nokoro 304 poli. N°4)<br>- after 20 minutes<br>- after 24 hours | 12<br>14        | FTM 1<br>FTM 1 |
| <b>Shear</b> on brushed stainless steel (ref. Nokoro 304 poli. N°4)<br>1kg – 25mm x 25mm (hours)                           | 500             | FTM 8          |

| CARRIER DATA | Typical Values* | Test Method |
|--------------|-----------------|-------------|
| Carrier Free |                 |             |

| TEMPERATURE RESISTANCE          | Typical Values*   | Test Method     |
|---------------------------------|-------------------|-----------------|
| Minimum Application Temperature | + 10°C            |                 |
| End-use Temperature Range       | - 30°C to + 100°C |                 |
| Short Term Resistance           | + 180°C           | S.A.F.T. 500grs |

| RELEASE LINER        | Typical Values* | Test Method |
|----------------------|-----------------|-------------|
| Clear PE Film        | 100µ            | ISO 536     |
| White Silicone Paper | 95 gr/sqm       | ISO 536     |

| THICKNESS          | Typical Values* | Test Method |
|--------------------|-----------------|-------------|
| Carrier + Adhesive | 43µ             | ISO 534     |

\*Values given are typical and are not necessarily for use in specifications.

### APPLICATION TECHNIQUES:

- It is essential with all pressure-sensitive tapes the application surface is clean, dry and free of grease and oil
- Bond strength is dependent upon the amount of adhesive-to-surface contact developed
- Note that different pressure, time and temperature on different (firm / rigid) surface achieves different performance

### IMPORTANT NOTICE:

Information on the above characteristics is based upon tests we believe to be reliable. The values given are typical values that vary according to application conditions. The values are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine prior to use the suitability of this material for their specific purposes. All Avery Dennison materials described herein are sold subject to Avery Dennison Conditions of Sales, a copy of which is available upon request.

Please refer to [Tapes.AveryDennison.com](https://www.tapes.averydennison.com) for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2017 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation. All other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation.



**Asia Pacific**  
Kunshan, China,  
No. 618 Nanhe Road  
Kunshan Economic &  
Technological Zone  
China 215335  
Phone: +86 512 57155001  
Fax: +86 512 57155059

**Europe**  
Tieblokkenlaan 1  
B-2300 Turnhout  
Belgium  
Phone: +32 (0)14 40 48 11  
Fax: +32 (0)14 40 48 55

Bld J.F. Kennedy 1  
7060 Soignies  
Belgium  
Phone: +32 (0)14 404 963  
Fax: +32 (0)14 40 48 55

**North America**  
250 Chester Street  
Painesville, Ohio  
44077 USA  
Phone: +1 866-462-8379  
Fax: +1 888-358-4469

For more information on our bonding tapes and adhesive solutions,  
visit [Tapes.AveryDennison.com](https://www.tapes.averydennison.com)