




FT T9020T

FT T9020T is part of a double-sided adhesive system especially designed for the assembly of membrane switches. The range consists of mounting tapes and spacer tapes of different thicknesses. All these products have superior stay-flat and die-cutting properties. They are available in roll and sheet form.

CONSTRUCTION & TYPICAL APPLICATION:

- Consists of a 125 μ polyester film coated on both sides with a solvent based pure acrylic adhesive. It offers high tack, high peel properties and high shear resistance.
- Protected by 2 moisture stable paper liners.
- Assembly of Membrane Switch Panels.



- Siliconised PE coated paper
- Solvent based pure acrylic adhesive
- PET film 125 μ
- Solvent based pure acrylic adhesive
- Siliconised PE coated paper

Adhesion with Substrates

Metal / Aluminium	High	Acrylic / PET	Medium
Glass / Ceramics	High	Polystyrene	Medium
Painted Surface	High	PP / PE / PS	Medium
Wood / Board / Paper	Medium	Textile / Cotton	Medium
Soft PVC	Medium	Rubber / EPDM	Medium
Rigid PVC	High	Smooth Substrate	Medium
PC / ABS	High	Rough Substrate	Medium

Chemical Properties

Copper corrosiveness	N.A.	Resistant to:	
Chlorine contents (ppm)	< 100	Water	Good
Sulphur contents (ppm)	< 100	Detergents	Good
		Dilute acids & alkalis	Good
		Concentrated alkalis	Poor
		Concentrated acids	Poor
		Aliphatic hydrocarbons	Good
		Ketones & esters	Fair
		Chlorinated hydrocarbons	Poor
		Aromatic Hydrocarbons	Poor

SHELF LIFE:

- 2 years when stored at 15/25° C and \pm 50% relative humidity.

FT T9020T

ADHESIVE DATA	Typical Values*	Test Method
Quick Tack (N/25mm) on brushed stainless steel (ref. Nokoro 304 poli. N°4)	30	FTM 9
Peel 180° (N/25mm) on brushed stainless steel (ref. Nokoro 304 poli. N°4) - after 20 minutes - after 24 hours	28 30	FTM 1 FTM 1
Shear on brushed stainless steel (ref. Nokoro 304 poli. N°4) 1kg – 25mm x 25mm (hours)	> 1000	FTM 8

CARRIER DATA	Typical Values*	Test Method
Thickness (μ)	125	ISO 534
Tensile (N/15mm)	MD 300 CD 300	DIN 53455
Elongation (%) (max)	MD 180 CD 180	DIN 53455

TEMPERATURE RESISTANCE	Typical Values*	Test Method
Minimum Application Temperature	+ 5°C	
End-use Temperature Range	- 40°C to + 180°C	

RELEASE LINER	Typical Values*	Test Method
White PE Coated Kraft Paper	100 gr/sqm, non printed	ISO 536
White PE Coated Kraft Paper	100 gr/sqm, printed in grey	ISO 536

THICKNESS	Typical Values*	Test Method
Carrier + Adhesive	225μ	ISO 534

*Values given are typical and are not necessarily for use in specifications.

APPLICATION TECHNIQUES:

- It is essential with all pressure-sensitive tapes the application surface is clean, dry and free of grease and oil
- Bond strength is dependent upon the amount of adhesive-to-surface contact developed
- Note that different pressure, time and temperature on different (firm / rigid) surface achieves different performance

IMPORTANT NOTICE:

Information on the above characteristics is based upon tests we believe to be reliable. The values given are typical values that vary according to application conditions. The values are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine prior to use the suitability of this material for their specific purposes. All Avery Dennison materials described herein are sold subject to Avery Dennison Conditions of Sales, a copy of which is available upon request.

Please refer to [Tapes.AveryDennison.com](https://www.tapes.averydennison.com) for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2017 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation. All other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation.



Performance
Tapes

Asia Pacific
Kunshan, China,
No. 618 Nanhe Road
Kunshan Economic &
Technological Zone
China 215335
Phone: +86 512 57155001
Fax: +86 512 57155059

Europe
Tieblokkenlaan 1
B-2300 Turnhout
Belgium
Phone: +32 (0)14 40 48 11
Fax: +32 (0)14 40 48 55

Bld J.F. Kennedy 1
7060 Soignies
Belgium
Phone: +32 (0)14 404 963
Fax: +32 (0)14 40 48 55

North America
250 Chester Street
Painesville, Ohio
44077 USA
Phone: +1 866-462-8379
Fax: +1 888-358-4469

For more information on our bonding tapes and adhesive solutions,
visit [Tapes.AveryDennison.com](https://www.tapes.averydennison.com)