



AFB™ 6125WI


Avery Dennison™ AFB™ 6125WI is white acrylic double coated foam tape with multipurpose acrylic adhesive on both sides. This firm foam adhesive offers strong lamination properties and good weather and environmental resistance. An additional layer of adhesive offers resistance of migration toward plasticizer in vinyl substrates. Suitable for a wide range of applications, including large domestic appliances, nameplate or sign bonding, and control panel mounting

FEATURES

- Foam tape with viscoelastic acrylic foam carrier
- Closed cell structure
- Acrylic adhesive system

BENEFITS

- High adhesion combined with good shear absorbs shock and distributes stress evenly
- Good moisture, UV and high temperature resistance
- Uniform bonding performance
- Helps eliminate the need for mechanical fasteners, drilling or grinding and related clean-up for certain applications
- Polyethylene liner helps provide good moisture stability and easier converting with its high tear strength



CONSTRUCTION:

Liner:

PE Coated White Paper with Imprinted Avery Logo

Adhesive 1:

Acrylic

Carrier:

White Acrylic Foam Core

Adhesive 2:

Acrylic

AFB™ 6125WI

Adhesive Properties:		Typical Values		
Thickness	ASTM D3652	US Mils	MM's	Micron's (µm)
Liner		6.3	0.16	160
Carrier & Adhesive		9.8	0.25	249
Total Caliper without Liner:		9.8	0.25	249
Total Caliper:		16.1	0.41	409

Peel Adhesion		ASTM D3330		
90° 12 in (300 mm) min @ Room Temp				
Substrate			Lbf / in	N / Meter
SS	Liner	20 min dwell	5.7	1,006
SS	Liner	72 hr dwell	9.1	1,610

Dynamic Shear		ASTM D1002		
180° 0.5 in (12.7 mm) / min @ Room Temp				
Substrate			Lbf / in	N / Meter
SS	Liner	72 hr dwell	116.0	20,428

Normal Tensile		ASTM D1002		
180° 2 in (50.8 mm) / min @ Room Temp				
Substrate			Lbf / in	N / Meter
Aluminum	Liner	72 hr dwell	87.0	15,324

Static Shear		ASTM D3654		
180° 1" sq (6.5 cm2) 500 g @ 194°F / 90°C				
Substrate			Min to Fail	
SS	Liner	Initial	> 10,000	

TEMPERATURES	° F	° C
Minimum Service Temperature	194° F	90° C
Maximum Service Temperature	302° F	150° C

THE LISTED VALUES ARE TYPICAL AND NOT INTENDED TO SERVE AS PRODUCT SPECIFICATIONS

APPLICATION TECHNIQUES

- It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied be clean, dry, and free of grease or oil
- Bond strength is dependent upon the amount of adhesive-to-surface contact developed
- Note that different pressure, time and temperature on different (film / rigid) surface achieves different performance

STORAGE / SHELF LIFE

- One year when stored at 64-72°F (18-22°C) / 30-70% relative humidity, out of direct sunlight and in original packaging.

Please refer to Tapes.AveryDennison.com for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2020 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation. All other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation.



Performance Tapes

Asia Pacific
Kunshan, China,
NO. 618 Nanhe Road
Kunshan Economic &
Technological Zone
China, 215335
Phone: +86 512 57155001
Fax: +86 512 57155059

Europe
Tieblokkenlaan 1
B-2300 Turnhout
Belgium
Phone: +32 (0)14 40 48 11
Fax: +32 (0)14 40 48 55

North America
250 Chester Street
Painesville, Ohio
44077 USA
Phone: +1 866-462-8379
Fax: +1 888-358-4469