



## AFB™ 6464W


Avery Dennison™ AFB™ 6464W is a white acrylic double coated foam tape, with acrylic adhesive for low surface energy substrates on both sides. This firm yet thin foam adhesive is a custom solution for low surface energy (LSE) substrates and features an additional layer of modified acrylic adhesive for good bonding to powder coated paints. The conformable foam density level enables good lamination on irregular substrates, and offers good weather and environmental resistance. Used for construction and mounting, attachments, and bonding of bumper rails and nameplates on low surface energy (LSE) materials.

### FEATURES

- Foam tape with viscoelastic acrylic foam carrier
- Closed cell structure
- Acrylic adhesive system

### BENEFITS

- High adhesion combined with good shear absorbs shock and distributes stress evenly
- Good moisture, UV and high temperature resistance
- Uniform bonding performance
- Helps eliminate the need for mechanical fasteners, drilling or grinding and related clean-up for certain applications
- Polyethylene liner helps provide good moisture stability and easier converting with its high tear strength



### CONSTRUCTION:

#### Liner:

Polyethylene Coated White Paper

#### Adhesive 1:

LSE Acrylic

#### Carrier:

White Acrylic Foam Core

#### Adhesive 2:

LSE Acrylic

**AFB™ 6464W**

Adhesive Properties:		Typical Values		
Thickness	ASTM D3652	US Mils	MM's	Micron's (µm)
Liner		6.3	0.16	160
Carrier & Adhesive		25.2	0.64	640
Total Caliper without Liner:		25.2	0.64	640
Total Caliper:		31.5	0.80	800

Peel Adhesion		ASTM D3330		
90° 12 in (300 mm) min @ Room Temp				
Substrate			Lbf / in	N / Meter
SS	Liner	20 min dwell	8.2	1,444
SS	Liner	72 hr dwell	13.6	2,395

Dynamic Shear		ASTM D1002		
180° 0.5 in (12.7 mm) / min @ Room Temp				
Substrate			Lbf / in	N / Meter
SS	Liner	72 hr dwell	118.9	20,938

Normal Tensile		ASTM D1002		
180° 2 in (50.8 mm) / min @ Room Temp				
Substrate			Lbf / in	N / Meter
Aluminum	Liner	72 hr dwell	116.8	20,568

Static Shear		ASTM D3654		
180° 1" sq (6.5 cm <sup>2</sup> ) 500 g @ 194°F / 90°C				
Substrate			Min to Fail	
SS	Liner	Initial	> 10,000	

TEMPERATURES	° F	° C
Minimum Service Temperature	212° F	100° C
Maximum Service Temperature	248° F	120° C

THE LISTED VALUES ARE TYPICAL AND NOT INTENDED TO SERVE AS PRODUCT SPECIFICATIONS

**APPLICATION TECHNIQUES**

- It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied be clean, dry, and free of grease or oil
- Bond strength is dependent upon the amount of adhesive-to-surface contact developed
- Note that different pressure, time and temperature on different (film / rigid) surface achieves different performance

**STORAGE / SHELF LIFE**

- One year when stored at 64-72°F (18-22°C) / 30-70% relative humidity, out of direct sunlight and in original packaging.

Please refer to [Tapes.AveryDennison.com](http://Tapes.AveryDennison.com) for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2020 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation. All other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation.



Performance  
Tapes

Asia Pacific  
Kunshan, China,  
NO. 618 Nanhe Road  
Kunshan Economic &  
Technological Zone  
China, 215335  
Phone: +86 512 57155001  
Fax: +86 512 57155059

Europe  
Tieblokkenlaan 1  
B-2300 Turnhout  
Belgium  
Phone: +32 (0)14 40 48 11  
Fax: +32 (0)14 40 48 55

North America  
250 Chester Street  
Painesville, Ohio  
44077 USA  
Phone: +1 866-462-8379  
Fax: +1 888-358-4469