



FM M2713 Clearback

FM M2713 Clearback is a pressure-sensitive fastening system consisting of a variety of cross linked, closed-cell, polyethylene foams in various thicknesses, densities and colors, and coated both sides with specifically formulated pressure-sensitive adhesives.

CONSTRUCTION & TYPICAL APPLICATION:

- Consists of a 2 mm black, cross-linked, closed-cell, polyethylene foam coated on both sides with an acrylic adhesive. It offers very high adhesion and cohesive properties.
- Produced in self-wound format on a clear siliconized PET 50µ.
- Foam tape with exceptional resistance to ageing, weathering, solvents. Recommended when a thicker foam is a must.



Adhesion with Substrates			
Metal / Aluminium	High	Acrylic / PET	Medium
Glass / Ceramics	High	Polystyrene	Medium
Painted Surface	Medium	PP / PE / PS	Medium
Wood / Board / Paper	Medium	Textile / Cotton	Medium
Soft PVC	Medium	Rubber / EPDM	Medium
Rigid PVC	Medium	Smooth Substrate	High
PC / ABS	High	Rough Substrate	Medium

RESISTANCE:

• Resistant to water, detergents, alcohol. Not recommended for use in contact with aliphatic and some aromatic solvents.

SHELF LIFE:

• 2 years when stored at $15/25^{\circ}$ C and \pm 50% relative humidity.



FM M2713 CLEARBACK

ADHESIVE DATA	Typical Values*	Test Method
Peel 180° (N/25mm) on brushed stainless steel (ref. Nokoro 304 poli. N°4) - after 20 minutes	> 20**	FTM 1
Shear on brushed stainless steel (ref. Nokoro 304 poli. N°4) 1kg – 25mm x 25mm (hours)	> 1000	FTM 8

CARRIER DATA	Typical Values*	Test Method
Tensile (N/15mm)	MD 27 CD 17,5	DIN 53455
Elongation (%) (max.)	MD 400 CD 400	DIN 53455
Density	Medium	

TEMPERATURE RESISTANCE	Typical Values*	Test Method
Minimum Application Temperature	+ 10°C	
End-use Temperature Range	- 40°C to + 95°C	

RELEASE LINER	Typical Values*	Test Method
Clear PET	50µ	ISO 536

THICKNESS	Typical Values*	Test Method
Carrier + Adhesive	2,1mm	ISO 534

^{*}Values given are typical and are not necessarily for use in specifications.

APPLICATION TECHNIQUES:

- It is essential with all pressure-sensitive tapes the application surface is clean, dry and free of grease and oil
- Bond strength is dependent upon the amount of adhesive-to-surface contact developed
- Note that different pressure, time and temperature on different (firm / rigid) surface achieves different performance

IMPORTANT NOTICE:

Information on the above characteristics is based upon tests we believe to be reliable. The values given are typical values that vary according to application conditions. The values are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine prior to use the suitability of this material for their specific purposes. All Avery Dennison materials described herein are sold subject to Avery Dennison Conditions of Sales, a copy of which is available upon request.

lease refer to Tapes.AveryDennison.com for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2017 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation.

All other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation



Performance

Asia Pacific

Kunshan, China, No. 618 Nanhe Road Kunshan Economic & Technological Zone China 215335 Phone: +86 512 57155001 Fax: +86 512 57155059

Europe Tieblokkenlaan 1

B-2300 Turnhout Belgium

Phone: +32 (0)14 40 48 11 Fax: +32 (0)14 40 48 55

Bld J.F. Kennedy 1 7060 Soignies Belgium Phone: +32 (0)14 404 963 Fax: +32 (0)14 40 48 55

North America 250 Chester Street Painesville, Ohio 44077 USA

Phone: +1 866-462-8379 Fax: +1 888-358-4469

^{**}Foam cleavage.