



FT 1149X 12 Pt Board


Avery Dennison™ FT 1149X 12 Pt Board is a 5.0 mil transfer tape with a high performance low VOC modified acrylic adhesive and a heavy board release liner. It bonds very well to low surface energy materials and features good foam bonding properties and high heat resistance. FT 1149X 12 Pt Board is commonly used in automotive applications and where low VOC properties are required.

FEATURES

- Unsupported adhesive
- Low outgassing high performance modified acrylic adhesive
- 12 point poly coated kraft board release liner

BENEFITS

- Highly conformable to curved or irregular surfaces
- Solvent free adhesive with good foam bonding performance
- Good heat resistance
- Heavyweight and stiffness allow for easy handling
- Two-year warranty



CONSTRUCTION:

Liner:

Natural 12 Pt Board

Adhesive:

Low VOC Acrylic

FT 1149X 12 Pt Board

Adhesive Properties:		Typical Values		
Thickness	ASTM D3652	US Mils	MM's	Micron's (µm)
Liner		12.9	0.33	328
Adhesive		5.0	0.13	127
Total Caliper without Liner:		5.0	0.13	127
Total Caliper:		17.9	0.45	455

Peel Adhesion		ASTM D3330		
180° 12 in (300 mm) min @ Room Temp				
Substrate		Lbf / in	N / Meter	
SS	72 hr dwell	10.0	1,761	

Peel Adhesion		ASTM D3330		
180° 12 in (300 mm) min @ Room Temp				
Substrate		Lbf / in	N / Meter	
ABS	72 hr dwell	10.0	1,761	

Loop Tack		ASTM D6195		
180° 32 in (508 mm) / min @ Room Temp				
Substrate		Lbf / in	N / Meter	
SS	Initial	5.0	881	

Static Shear		ASTM D3654		
180° 1" sq (6.5 cm ²) 500 g @ Room Temp				
Substrate		Min to Fail		
SS	Liner 24 hr dwell	> 10,000		

TEMPERATURES	° F	° C
Minimum Application Temperature	50° F	10° C
Minimum Service Temperature	-40° F	-40° C
Maximum Service Temperature	350° F	175° C

THE LISTED VALUES ARE TYPICAL AND NOT INTENDED TO SERVE AS PRODUCT SPECIFICATIONS

APPLICATION TECHNIQUES

- It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied be clean, dry, and free of grease or oil
- Bond strength is dependent upon the amount of adhesive-to-surface contact developed
- Note that different pressure, time and temperature on different (film / rigid) surface achieves different performance

STORAGE / SHELF LIFE

- Two years when stored at 64-72°F (18-22°C) / 30-70% relative humidity, out of direct sunlight and in original packaging.

Please refer to Tapes.AveryDennison.com for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2020 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation. All other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation.



Performance
Tapes

Asia Pacific
Kunshan, China,
NO. 618 Nanhe Road
Kunshan Economic &
Technological Zone
China, 215335
Phone: +86 512 57155001
Fax: +86 512 57155059

Europe
Tieblokkenlaan 1
B-2300 Turnhout
Belgium
Phone: +32 (0)14 40 48 11
Fax: +32 (0)14 40 48 55

North America
250 Chester Street
Painesville, Ohio
44077 USA
Phone: +1 866-462-8379
Fax: +1 888-358-4469