

TECHNICAL DATA SHEET

Avery Dennison™ FT 2014 is a dispersion-based modified acrylic transfer tape, used for bonding polyurethane foam, polyester fibers, felts and fabrics to a wide variety of substrates. Provides high adhesion to medium and low surface energy materials such as PP, PE, TPO, ABS, PVC, polystyrene and painted metals. Ideal for general purpose foam bonding applications such as gaskets, sound deadening and insulation materials in automotive, building and construction, appliance assembly and general industrial sub-assembly.

FEATURES

- Dispersion-based modified acrylic adhesive
- APEO free adhesive
- High initial tack
- Easy release glassine liner
- Broad range of service temperatures

BENEFITS

- Excellent resistance to solvents, chemicals, plasticizers, temperature and UV light
- Medium resistance to moisture
- Good conformability to flat or curved surfaces
- Immediate initial adhesion for part placement
- Excellent water jet and die cutting characteristics



CONSTRUCTION

Liner: White glassine liner

Adhesive: Dispersion-based modified acrylic



Performance
Tapes

Adhesive Properties**Typical Values**

THICKNESS (ASTM D3652)		US Mil's	MM's	Micron's (µm)
Liner		2.64	0.067	67
Adhesive		1.57	0.040	40
Total Caliper		4.21	0.107	107
PEEL ADHESION (ASTM D3330) 180° (12") 300 mm / min @ Room Temp				
SUBSTRATE		Lbf / in	US Oz / In	N / Meter
Stainless Steel	72 hr dwell	5.14	82	900
ABS	72 hr dwell	4.57	73	800
Polypropylene	72 hr dwell	4.00	64	700
LOOP TACK (ASTM D6195) (12") 300 mm / min @ Room Temp				
SUBSTRATE		Lbf / in	US Oz / In	N / Meter
Stainless Steel	Initial	4.57	73	800
Finat tack	Initial	4.57	73	800
TEMPERATURES			°F	°C
Minimum Application Temperature			50 °F	10 °C
Minimum Service Temperature			-40 °F	-40 °C
Maximum Service Temperature			266 °F	130 °C

Note: The listed values are typical only and not intended to serve as product specifications

APPLICATION TECHNIQUES

- It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied be clean, dry, and free of grease or oil
- Bond strength is dependent upon the amount of adhesive-to-surface contact developed
- Note that different pressure, time and temperature on different (film / rigid) surface achieves different performance

STORAGE / SHELF LIFE

Two years when stored at 64-72 °F (18-22 °C) / 30-70 % relative humidity, out of direct sunlight and in original packaging.

For more information on our bonding tapes and adhesive solutions, call us:

North America: +1 866 462 8379

Asia Pacific: +86 512 57155001

Europe: +32 (0)14 40 48 11

www.tapes.averydennison.com