

TECHNICAL DATA SHEET

Avery Dennison™ FT 2055 is a dispersion-based modified acrylic transfer tape used for bonding polyurethane foam, polyester fibers, felts and fabrics to a wide variety of substrates. Provides high adhesion to medium and low surface energy materials such as PP, PE, TPO, ABS, PVC, polystyrene and painted metals. Ideal for general purpose foam bonding applications such as gaskets, sound deadening and insulation materials in automotive, building and construction, appliance assembly and general industrial sub-assembly.

FEATURES

- Dispersion-based modified acrylic adhesive
- APEO free adhesive
- High initial tack
- Easy release OPP film liner
- Broad range of service temperatures

BENEFITS

- Excellent resistance to solvents, chemicals, plasticizers, temperature and UV light
- Medium resistance to moisture
- Good conformability to flat or curved surfaces
- Immediate initial adhesion for part placement
- Excellent water jet and die cutting characteristics



CONSTRUCTION

Liner: White OPP film liner

Adhesive: Dispersion-based modified acrylic



Performance
Tapes

Adhesive Properties**Typical Values**

THICKNESS (ASTM D3652)	US Mil's	MM's	Micron's (µm)
Liner	2.36	0.060	60
Adhesive	1.97	0.050	50
Total Caliper	4.33	0.110	110
PEEL ADHESION (ASTM D3330)			
180° (12") 300 mm / min @ Room Temp			
SUBSTRATE		Lbf / in	N / Meter
Stainless Steel	72 hr dwell	6.28	1100
ABS	72 hr dwell	5.71	1000
Polypropylene	72 hr dwell	5.14	900
LOOP TACK (ASTM D6195)			
(12") 300 mm / min @ Room Temp			
SUBSTRATE		Lbf / in	N / Meter
Glass		5.14	900
TEMPERATURES		°F	°C
Minimum Application Temperature		50 °F	10 °C
Minimum Service Temperature		-40 °F	-40 °C
Maximum Service Temperature		266 °F	130 °C

Note: The listed values are typical only and not intended to serve as product specifications

APPLICATION TECHNIQUES

- It is essential with all pressure-sensitive tapes the application surface is clean, dry and free of grease and oil
- Bond strength is dependent upon the amount of adhesive-to-surface contact developed
- Note that different pressure, time and temperature on different (firm / rigid) surface achieves different performance

STORAGE / SHELF LIFE

One year when stored at 64-72 °F (18-22 °C) / 30-70 % relative humidity, out of direct sunlight and in original packaging.

For more information on our bonding tapes and adhesive solutions, call us:

North America: +1 866 462 8379

Asia Pacific: +86 512 57155001

Europe: +32 (0)14 40 48 11

www.tapes.averydennison.com