



## FT 7338L

Avery Dennison FT 7338L is a 150 micron double coated film tape featuring a modified acrylic adhesive with a clear PET carrier. The specially designed adhesive offers well balanced performance designed for component mounting in mobile phone assembly.

### FEATURES:

- Modified acrylic adhesive
- Clear PET carrier
- Glassine liner

### BENEFITS:

- High adhesion on a variety of substrates, including low surface energy materials
- Excellent cohesion provide high dynamic shear and push out force
- High temperature and UV light resistance
- Provides dimensional stability and excellent water jet and die cutting performance
- Waterproof with IPX7 certification



### CONSTRUCTION:

#### Liner:

Havana glassine with Avery Dennison logo

#### Adhesive:

Modified acrylic

#### Carrier:

Clear PET

#### Adhesive:

Modified acrylic

## FT 7338L

Adhesive Properties	Typical Values		
	US Mils	mm	Microns (µm)
<b>THICKNESS</b>			
Adhesive + Carrier	5.9	0.15	150
Liner	3.0	0.08	78
Total	8.9	0.23	228

\*PSTC-133

### PEEL ADHESION

2 mil PET; 180°; 12" / min

Substrate	Lbf / in		N / 25mm	
	20 min	24 hr	20 min	24 hr
Stainless steel	5.7	6.4	25	28
Polycarbonate	6.8	8.7	30	32

\*PSTC-101, ASTM D-3330, STD-10

### LOOP TACK

2 mil PET; 90°; 20" / min; 1" sq (6.5 cm<sup>2</sup>)

Substrate	Lbf / in		N / 25mm	
Stainless steel	6.8		30	

\*PSTC-16, STD-7

### STATIC SHEAR

Foil; 1" sq (6.5 cm<sup>2</sup>); 1000 g

#### Min to Fail

>10,000

\*PSTC-107, ASTM D 3654, STD-9

### TEMPERATURES

Min. Application Temp.	50 ° F	10 ° C
Max. Continuous Operating Temp.	212 ° F	100 ° C
Max. Intermittent Operating Temp.	248 ° F	120 ° C

\*TEST METHODS

Note: The listed values are typical only and not intended to serve as product specifications

## APPLICATION TECHNIQUES

- It is essential with all pressure-sensitive tapes the application surface is clean, dry and free of grease and oil
- Bond strength is dependent upon the amount of adhesive-to-surface contact developed
- Note that different pressure, time and temperature on different (firm / rigid) surface achieves different performance

## STORAGE AND SHELF LIFE

The shelf life of the product is two years when stored at 18-22°C / 64-72°F, 30-70% relative humidity and out of direct sunlight, in original packaging.

Please refer to [Tapes.AveryDennison.com](http://Tapes.AveryDennison.com) for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2016 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation. All other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation.



Performance  
Tapes

Asia Pacific  
Kunshan, China,  
NO. 618 Nanhe Road  
Kunshan Economic &  
Technological Zone  
China, 215335  
Phone: +86 512 57155001  
Fax: +86 512 57155059

Europe  
Tieblokkenlaan 1  
B-2300 Turnhout  
Belgium  
Phone: +32 (0)14 40 48 11  
Fax: +32 (0)14 40 48 55

North America  
250 Chester Street  
Painesville, Ohio  
44077 USA  
Phone: +1 866-462-8379  
Fax: +1 888-358-4469

For more information on our bonding tapes and adhesive solutions, visit [Tapes.AveryDennison.com](http://Tapes.AveryDennison.com)