

TECHNICAL DATA SHEET

Avery Dennison™ FT 7995 is a double coated scrim tape with a dispersion-based modified acrylic adhesive used for bonding polyurethane foam, polyester fibers, felts and fabrics to a wide variety of substrates. Provides high adhesion to medium and low surface energy materials such as PP, PE, TPO, ABS, PVC, polystyrene and painted metals. Ideal for general purpose foam bonding applications such as gaskets, sound deadening and insulation materials in automotive, building and construction, appliance assembly and general industrial sub-assembly.

FEATURES

- Dispersion-based modified acrylic adhesive
- APEO free adhesive
- High initial tack
- Easy release glassine liner
- Broad range of service temperatures
- Polyester scrim reinforcement

BENEFITS

- Excellent resistance to solvents, chemicals, plasticizers, temperature and UV light
- Medium resistance to moisture
- Good conformability to flat or curved surfaces
- Immediate initial adhesion for part placement
- Excellent water jet and die cutting characteristics
- Helps provide tear resistance



CONSTRUCTION

Liner: Havana (yellow/brown) glassine liner

Adhesive 1: Dispersion-based modified acrylic

Carrier: Polyester scrim

Adhesive 2: Dispersion-based modified acrylic



Performance
Tapes

Adhesive Properties

Typical Values

THICKNESS (ASTM D3652)		US Mils	MM's	Micron's (µm)
Liner		2.64	0.067	67
Carrier & Adhesive		5.31	0.135	10 + 125
Total Caliper		7.95	0.202	202
PEEL ADHESION (ASTM D3330)				
180° (12") 300 mm / min @ Room Temp				
SUBSTRATE		Lbf / in	US Oz / In	N / Meter
Stainless Steel	20 min dwell			
	72 hr dwell	8.57	137	1500
Polycarbonate				
20 min dwell				
72 hr dwell		7.99	128	1400
ABS				
20 min dwell				
74 hr dwell		7.42	119	1300
Polypropylene				
20 min dwell				
74 hr dwell				
LOOP TACK (ASTM D6195)				
(12") 300 mm / min @ Room Temp				
SUBSTRATE		Lbf / in	US Oz / In	N / Meter
Stainless Steel	Initial	5.71		1000
	Final tack	5.71		1000
STATIC SHEAR (ASTM D3654)				
1"sq (6.25 cm ²) 1000 g @ Room Temp				
SUBSTRATE		Min to Fail		
Stainless Steel	Initial	> xxx		
TEMPERATURES				
		°F	°C	
Minimum Application Temperature		50 °F	10 °C	
Minimum Service Temperature		-40 °F	-40 °C	
Maximum Service Temperature		266 °F	130 °C	

Note: The listed values are typical only and not intended to serve as product specifications

APPLICATION TECHNIQUES

- It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied be clean, dry, and free of grease or oil
- Bond strength is dependent upon the amount of adhesive-to-surface contact developed
- Note that different pressure, time and temperature on different (film / rigid) surface achieves different performance

STORAGE / SHELF LIFE

Two years when stored at 64-72 °F (18-22 °C) / 30-70 % relative humidity, out of direct sunlight and in original packaging.

For more information on our bonding tapes and adhesive solutions, call us:

North America: +1 866 462 8379

Asia Pacific: +86 512 57155001

Europe: +32 (0)14 40 48 11

www.tapes.averydennison.com