FT 8397

Avery Dennison™ FT 8397 was designed for applications requiring quick stick and good adhesion to plastics and other low surface energy substrates.

FEATURES

- Polyester carrier
- · Specially formulated acrylic adhesive
- · Densified kraft release liner

BENEFITS

- · Excellent processing and die-cutting stability
- Good adhesion and tack to low surface energy substrates
- Adhesive resists mild plasticizers and environmental exposures
- Made in the USA



CONSTRUCTION:

Liner:

60# White Kraft

Adhesive 1:

Acrylic

Carrier:

Polyester

Adhesive 2:

Acrylic

FT 8397

Adhesive Properties:

Autiesive Properties.				i ypicai vaiues		
Thickness		ASTM D3652	US Mils	MM's	Micron's (µm)	
Liner			3.5	0.09	89	
Adhesive 1 - Liner			1.0	0.03	25	
Carrier			0.5	0.01	13	
Adhesive 2 - Unwind			1.2	0.03	30	
Total Caliper without Lir	ner:		2.7	0.07	69	
Total Caliper:			6.2	0.16	157	
Peel Adhesion		ASTM D3330				
180° 12 in (305 mm) /	min					
Substrate			Lbf / In		N / Meter	
SS	Liner	Initial	6.3		1,109	
	Unwind		6.8		1,197	
ABS	Liner	Initial	4.9	863		
	Unwind		5.7	1,004		
PP	Linar	Initial	5.6	986		
	Liner	IIIIIIIII	5.6	900		
	Unwind		5.∠	910		
Talo DD	Liner	Initial	3.3		581	
Talc PP	Unwind	IIIIIIai	3.4	599		
	Onwind		3.4	299		
HDPE	Liner	Initial	2.6	458		
	Unwind	IIIIIIIII	3.4	599		
	Onwind		5.7	399		
ТРО	Liner	Initial	4.8		845	
	Unwind	Titte	5.2	916		
	Onwind		0.2		010	
Painted Metal	Liner	Initial	3.9		687	
	Unwind		4.2			
				-	-	
Loop Tack		ASTM D6195				
180° 20 in (508 mm) /	/ min					
Substrate			Lbf / In		N / Meter	
SS	Liner	Initial	9.0		1,585	
	Unwind		7.9	7.9		
Static Shear		ASTM D3654				
180° 1" sq (6.5 cm2)	2500 g @ Room	Temp				
Substrate			Mins to Fail			
SS	Liner	Initial	> 150			
	Unwind		> 150			
SAFT		STD-243				
1" sq (6.5 cm2) 1000	g					
Substrate			Mins to Fail	Fail Temp °F	Fail Temp °C	
SS	Liner	24 hr dwell	104	156	69	
	Unwind		104	156	69	
TEMPERATURES			°F		° C	
Minimum Application Temperature			50° F		10° C	
Minimum Service Temp	perature		-40° F		-40° C	

Maximum Service Temperature 350° F

THE LISTED VALUES ARE TYPICAL AND NOT INTENDED TO SERVE AS PRODUCT SPECIFICATIONS

APPLICATION TECHNIQUES

- It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied be clean, dry, and free of grease or oil
- Bond strength is dependent upon the amount of adhesive-to-surface contact developed
- Note that different pressure, time and temperature on different (film / rigid) surface achieves different performance

STORAGE / SHELF LIFE

One year when stored at 64-72°F (18-22°C) / 30-70% relative humidity, out of direct sunlight and in original packaging.

Please refer to Tapes. Avery Dennison. com for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2020 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation. All other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation.



North America

175° C

Typical Values