# FASSON® 0817

Avery Dennison FASSON® 0817 is suitable for die-cut shapes, shielding, moisture and vapor barrier sealing components or lamination to insulation materials.

## **FEATURES**

- Dead-soft 2 mil foil facestock
- · Quick stick, cold-temperature rubber adhesive
- Strong bleached densified kraft liner



# **BENEFITS**

- Strong bond to a variety of substrates
- · Conformability to curved surfaces
- Exceptional cold environment adhesion conditions
- Tested in accordance with UL 723
- Made in the USA

# **CONSTRUCTION:**

Liner:

50# White Kraft

Adhesive:

Rubber

Carrier:

Aluminum Foil



General Use Tape Surface Burning Characteristcs to

UL 723 Flame Spread 10

722S Smoke Developed 15



# FASSON® 0817 Adhesive Properties: Typical Values Thickness ASTM D3652 US Mils MM's Micron's (μm) Liner 3.2 0.08 81 Adhesive 2.0 0.05 51

| 111101111000                 | 7.0.1 20002 |     |      | mioron o (pini) |
|------------------------------|-------------|-----|------|-----------------|
| Liner                        |             | 3.2 | 0.08 | 81              |
| Adhesive                     |             | 2.0 | 0.05 | 51              |
| Carrier                      |             | 2.0 | 0.05 | 51              |
|                              |             |     |      |                 |
|                              |             |     |      |                 |
| Total Caliper without Liner: |             | 4.0 | 0.10 | 102             |
| Total Caliper:               |             | 7.2 | 0.18 | 183             |
|                              |             |     |      |                 |

| Peel Adhesion             | ASTM D3330 |          |           |
|---------------------------|------------|----------|-----------|
| 180° 12 in (300 mm) min @ | Room Temp  |          |           |
| Substrate                 |            | Lbf / in | N / Meter |
| SS                        | Initial    | 4.9      | 863       |
|                           |            |          |           |
|                           |            |          |           |
|                           |            |          |           |
|                           |            |          |           |
|                           |            |          |           |
|                           |            |          |           |
|                           |            |          |           |
|                           |            |          |           |
|                           |            |          |           |
|                           |            |          |           |
| Loop Took                 | ACTM DG10E |          |           |

| Loop Tack                 | ASTM D6195  |          |           |
|---------------------------|-------------|----------|-----------|
| 180° 20 in (508 mm) / min | @ Room Temp |          |           |
| Substrate                 |             | Lbf / in | N / Meter |
| SS                        | Initial     | 12.0     | 2,113     |
|                           |             |          |           |
|                           |             |          |           |
|                           |             |          |           |
|                           |             |          |           |
|                           |             |          |           |
|                           |             |          |           |
|                           |             |          |           |
|                           |             |          |           |
|                           |             |          |           |

| A0714 D0054           |                                  |                         |  |
|-----------------------|----------------------------------|-------------------------|--|
|                       |                                  |                         |  |
| @ Room Temp           |                                  |                         |  |
| Substrate Min to Fail |                                  |                         |  |
| Initial               | > 10,000                         |                         |  |
|                       |                                  |                         |  |
|                       |                                  |                         |  |
|                       |                                  |                         |  |
|                       |                                  |                         |  |
|                       |                                  |                         |  |
|                       |                                  |                         |  |
|                       |                                  |                         |  |
|                       |                                  |                         |  |
|                       |                                  |                         |  |
|                       |                                  |                         |  |
|                       | ASTM D3654  @ Room Temp  Initial | @ Room Temp Min to Fail |  |

| TEMPERATURES                               | °F     | ° C   |
|--|--------|-------|
| Minimum Application Temperature            | 50° F  | 10° C |
| Maximum Continuous Operating Temperature   | 175° F | 79° C |
| Maximum Intermittent Operating Temperature | 200° F | 95° C |

THE LISTED VALUES ARE TYPICAL AND NOT INTENDED TO SERVE AS PRODUCT SPECIFICATIONS

### **APPLICATION TECHNIQUES**

- It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied be clean, dry, and free of grease or oil
- Bond strength is dependent upon the amount of adhesive-to-surface contact developed
- · Note that different pressure, time and temperature on different (film / rigid) surface achieves different performance

### STORAGE / SHELF LIFE

One year when stored at 64-72°F (18-22°C) / 30-70% relative humidity, out of direct sunlight and in original packaging.

Please refer to Tapes. Avery Dennison.com for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2022 Avery Dennison® Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison® Corporation. All other Avery Dennison® brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison® Corporation.



Performance

Asia Pacific Kunshan, China, NO. 618 Nanhe Road Kunshan Economic & Technological Zone China, 215335

Phone: +86 512 57155001 Fax: +86 512 57155059 Europe Tieblokkenlaan 1 B-2300 Turnhout Belgium

Phone: +32 (0)14 40 48 11 Fax: +32 (0)14 40 48 55

North America 250 Chester Street Painesville, Ohio 44077 USA Phone: +1 866-462-8379

Fax: +1 888-358-4469